

### product data

#### SELECTION & SPECIFICATION DATA

<b>TYPE &amp; DESCRIPTION</b>	133 Decorative Broadcast System is a 100% solids epoxy flooring system, designed for application over smooth substrates, at 1/8" nominal film thickness.
<b>ADVANTAGES</b>	Cures quickly to form an exceptionally tough, impact and abrasion resistant system, cured at temperatures as low as 50°F. Excellent adhesion to concrete, steel, and wood. Minimum down time. Sanitary, non-shrinking polymer. Easy to clean - USDA acceptable.
<b>CHEMICAL RESISTANCE</b>	Not affected by water, oil, brine, most acids, and alkalines. For specific recommendations, please refer to Greenstone's Chemical Resistance Guide, or contact Technical Service.
<b>USES</b>	Used as part of a polymer system for resurfacing floors in food production plants, aisle ways, chemical spill containment area's, industrial production facilities, and pulp and paper mills.
<b>GOVERNMENT AGENCY</b>	Meets the requirements of the U.S. Department of Agriculture (USDA) for use as an incidental food contact flooring system.

**FOR INDUSTRIAL USE ONLY!**

<b>PHYSICAL DATA</b>	<p>Working Time - Broadcast - 20-30 minutes at 75°F. Topcoat - 30-40 minutes at 75°F. Potlife - Broadcast - 15 minutes at 75°F. Topcoat - 30 minutes at 75°F. Cure Time - 133 Basecoat will harden within 4-8 hours at 75°F. 133 Topcoat will harden within 8-12 hours at 75°F. The warmer the temperature, the faster each component will cure. Allow a minimum cure of 24 hours for light traffic, and 96 hours for heavy traffic loads and chemical spillage. Solids - 100% Colors - Numerous color combinations (contact Sales for details)</p>
----------------------	---

<b>PACKAGING / COVERAGE</b>	<p><b><i>133 DECORATIVE BROADCAST SYSTEM is applied in two 133 BASECOATS, with one 133 TOPCOAT. The system (two BASECOATS and one TOPCOAT) requires approximately 1# of DECORATIVE AGGREGATE, per square foot to reach the nominal 1/8" film thickness.</i></b></p>
-----------------------------	---

**Components - 133 Basecoat, 133 Topcoat, Decorative Aggregate - each sold separately.**

***133 Basecoats - (two are required)***

***1 GALLON KIT - covers approximately 100 square feet at 16 mils -***

***1 container - Part A (resin)***

***1 container - Part B (hardener)***

***3 GALLON KIT - covers approximately 300 square feet at 16 mils -***

***1 container - Part A (resin)***

***1 container - Part B (hardener)***

***133 Topcoat - (required)***

***1 GALLON KIT - covers approximately 100 square feet at 16 mils -***

***1 container - Part A (resin)***

***1 container - Part B (resin)***

***2 GALLON KIT - covers approximately 200 square feet at 16 mils -***

***1 container - Part A (resin)***

***1 container - Part B (resin)***

***Decorative Aggregate - (Required) 1# per square foot for installed system.***

<b>SUPPLEMENTAL PRODUCTS</b>	133 Decorative Coving System, 350 Grout, 110 Surfacer.
------------------------------	--

## SURFACE PREPARATION

**New Concrete:** must have a minimum of 28 days cure, and no curing agents or sealers shall be used. Remove oil, grease or other loose or foreign materials and contaminants. A good bonding tooth, the texture of rough sandpaper, is required to maximize adhesion, with the removal of all glaze. Examples of mechanical surface prep including, but not limited to -

- A. Sandblast with steel shot, fine silica, or other similar material.
- B. Wheel Abrader
- C. Scarify

**Existing Concrete:** remove all loose, weak concrete, and any paint wax, oil, grease or other contaminants. Once the concrete has been cleaned and neutralized, mechanical surface preparation shall be used to provide a good bonding tooth, a texture of rough sandpaper, with the removal of all glaze. Examples of mechanical surface preparation including, but not limited to -

- A. Sandblast with steel shot, fine silica, or other similar material.
- B. Wheel Abrader
- B. Scarify

**Note:** Holes and depressions 1/4" or deeper should be prefilled with 350 grout, or a similar system, prior to application. All surfaces must be dry prior to application of polymer system.

**Metal Surfaces:** Degrease surface prior to sandblasting. Use organic solvents, alkaline solutions, steam, hot water with detergents, or other systems that will completely remove dirt, oil, grease, etc. Blast the surface to near white SSPC-SP 10-70, or NACE No. 2 using a Venturi blast nozzle with 100psi air. To produce the 4 mil minimum anchor pattern or tooth, the blasting media used shall be a properly graded, clean, sharp angular abrasive similar to Humble Abrasive Flint S7 (6-30 mesh), Steel Grit (HG25), or Black Beauty (BB1040).

## MIXING AND EQUIPMENT

### MIXING

**133 Decorative Broadcast / Topcoat** - Mix Part A and B thoroughly, with a low rpm "jiffy" type mixer for 2 minutes, until homogeneous.

**Important!** - The working life of the mixed blends is approximately 25 minutes. Mixed materials remaining in a container will produce heat. Do not reseal mixed containers!

## APPLICATION AND SAFETY

### APPLICATION

**Caution!** Application in direct sunlight, resulting in rising surface temperature, may cause blistering of the materials due to expansion of entrapped air or moisture in the concrete. Concrete surfaces that have been in direct sunlight must be shaded for 24 hours prior to application, and remain shaded until the initial set of the polymer. When the substrate temperature is rising, it is recommended to postpone application.

**Minimum application temperature:** Do not apply when substrate temperature is below 50°F.

For application, the 133 Broadcast & Topcoat resin & hardener should be at a minimum temperature of 70°F. Always spread the material as soon as blended. The pot life is approximately 10 minutes, and the working life is approximately 25 minutes.

**133 BASECOAT:** Spread the mixture with a medium (3/8") nap roller at a rate of 80 square feet per gallon (20 mils).

**SEED COAT:** Immediately broadcast the Decorative Aggregate into the BROADCAST coat at a rate of approximately 1/2# per square foot, or until the base coat is completely covered without any visible wet or shiny spots. Allow the polymer to cure until the loose sand can be removed without disturbing the base coat.

**CURE TIME** - Greenstone 133 Broadcast will harden in 4-8 hours at 75°F. The warmer the temperature, the faster the cure. Allow 24 hours, at 75°F, for light traffic, and 96 hours for full cure.

**2ND 133 Decorative Broadcast:** Spread the mixture with a medium (3/8") nap roller at a rate of 80 square feet per gallon (20 mils).

**2ND SEED COAT:** Immediately broadcast the Decorative Aggregate into the BROADCAST coat at a rate of approximately 1/2# per square foot, or until the base coat is completely covered without any visible wet or shiny spots. Allow the polymer to cure until the loose sand can be removed without disturbing the base coat.

**133 Decorative Topcoat:** Spread the mixture with a medium (3/8") nap roller at a rate of 80 square feet per gallon (20 mils) and backroll until roller marks are removed.

**CLEAN-UP** - Cured or hardened Greenstone 133 Decorative Broadcast is almost impossible to remove. Clean tools and equipment immediately with hot soapy water, or a mixture of acetone and ethanol.

### SAFETY

Observe good personal hygiene. Certain personnel may be sensitive to various types of resins which may cause dermatitis. Avoid contact with skin and breathing of vapor. Read and follow all caution statements on product info bulletin, material safety data sheet and container labels for this product. This bulletin provides standard information for the system and application procedure. Since varying application conditions may not be covered, consult GREENSTONE Technical Service Department for further information.

We guarantee our product to be free of defects in material and workmanship, and to be in accordance with our company quality control standards. All data, statements and recommendations made herein are based upon information we believe to be reliable, but are made without any representation or guarantee or warranty of accuracy and are made with reservation of all patent rights. Our products are sold on the condition that the user will evaluate them, as well as our recommendations, to determine their suitability for his own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only. No liability is assumed or implied, for injury to personnel, labor costs, product loss or any other expenses incidental to the structure or operation of the plant and equipment where the system is being applied.