



*product data*

**SELECTION & SPECIFICATION DATA**

<b>TYPE &amp; DESCRIPTION</b>	652 is a two component, high performance Novolac Vinylester coating system, formulated with exceptional corrosion protection while providing a tough wear-resistant surface.
<b>ADVANTAGES</b>	Cures quickly to form an exceptionally tough, impact and abrasion resistant system, cured at temperatures as low as 60°F. Excellent adhesion to concrete, steel, and wood. Minimum down time.
<b>CHEMICAL RESISTANCE</b>	Not affected by water, oil, brine, most acids, and alkalines. For specific recommendations, please refer to Greenstone's Chemical Resistance Guide, or contact Technical Service.
<b>USES</b>	Used as part of a polymer system for interior and exterior of tanks, walls, columns, curbs, pump pads, equipment and structural steel.
<b>GOVERNMENT AGENCY</b>	Meets the requirements of the U.S. Department of Agriculture (USDA) for use as an incidental food contact flooring system.

**FOR INDUSTRIAL USE ONLY!**

<b>PHYSICAL DATA</b>	<p><b>Compressive Strength - 16,000 psi (resin)</b>  <b>Tensile Strength - 13,300 psi (resin)</b>  <b>Impact Strength - 100 in./lbs.</b>  <b>Indentation - No indentation MIL-D-3134F</b>  <b>Abrasion Resistance - 68 milligrams ASTM D-1044</b>  <b>Maximum Temperatures - Wet Exposure 190°F, Dry Heat 300°F</b>  <b>Shelf Life - 1 Year (warehouse conditions)</b>  <b>Working Time - approximately 45 minutes at 75°F.</b>  <b>Potlife - approximately 30 minutes at 75°F.</b>  <b>Cure Time - hardens in 8-12 hours at 75°F. The warmer the temperature, the faster it cures. Allow a minimum cure of 24 hours for light traffic, and 96 hours for heavy traffic loads and chemical spillage.</b>  <b>Solids - 98% by weight, 98% by volume.</b>  <b>Appearance - Matte Finish</b>  <b>Colors - Dark Gray, Tile Red</b></p>
----------------------	---

**Recommended Film Thickness -**

- Fume Exposure - 16-20 mils. Applied in two coats.**
- Immersion - 24-30 mils. Applied in three coats.**

<b>PACKAGING / COVERAGE</b>	<p><b>652 Topcoat -</b></p> <p><b>1 GALLON KIT - covers approximately 100 square feet at 16 mils - containing the following -</b>  <b>1 container - Part A (resin)</b>  <b>1 container - Part B (hardener)</b></p> <p><b>5 GALLON KIT - covers approximately 500 square feet at 16 mils - containing the following -</b>  <b>1 container - Part A (resin)</b>  <b>1 container - Part B (resin)</b></p>
-----------------------------	--

<b>SUPPLEMENTAL PRODUCTS</b>	500 & 600 Series Primer, 620 Flooring System, 550 Grout, 662 Lining System.
------------------------------	---

## SURFACE PREPARATION AND SUBSTRATES

### SURFACE PREPARATION

**New Concrete:** must have a minimum of 28 days cure, and no curing agents or sealers shall be used. Remove oil, grease or other loose or foreign materials and contaminants. A good bonding tooth, the texture of rough sandpaper, is required to maximize adhesion, with the removal of all glaze. Examples of mechanical surface prep including, but not limited to -

- A. Sandblast with steel shot, fine silica, or other similar material.
- B. Wheel Abrader
- C. Scarify

**Existing Concrete:** remove all loose, weak concrete, and any paint wax, oil, grease or other contaminants. Once the concrete has been cleaned and neutralized, mechanical surface preparation shall be used to provide a good bonding tooth, a texture of rough sandpaper, with the removal of all glaze. Examples of mechanical surface preparation including, but not limited to -

- A. Sandblast with steel shot, fine silica, or other similar material.
- B. Wheel Abrader
- B. Scarify

Note: Holes and depressions should be prefilled, prior to application of 652. All surfaces must be dry prior to application of polymer system.

**Metal Surfaces:** Degrease surface prior to sandblasting. Use organic solvents, alkaline solutions, steam, hot water with detergents, or other systems that will completely remove dirt, oil, grease, etc. Blast the surface to near white SSPC-SP 10-70, or NACE No. 2 using a Venturi blast nozzle with 100psi air. To produce the 4 mil minimum anchor pattern or tooth, the blasting media used shall be a properly graded, clean, sharp angular abrasive similar to Humble Abrasive Flint S7 (6-30 mesh), Steel Grit (HG25), or Black Beauty (BB1040).

## MIXING AND EQUIPMENT

### MIXING

Mix Part A and B thoroughly, with a low rpm "jiffy" type mixer for 2 minutes until completely homogeneous. \*Product may be thinned up to 10% with MEK for improved application properties.

**Important!** - The working life of the mixed blend is approximately 25 minutes. Mixed materials remaining in a container will produce heat. Keep away from combustible materials. Do not reseal mixed containers!

## APPLICATION AND SAFETY

### APPLICATION

**Caution!** Application in direct sunlight, resulting in rising surface temperature, may cause blistering of the materials due to expansion of entrapped air or moisture in the concrete. Concrete surfaces that have been in direct sunlight must be shaded for 24 hours prior to application, and remain shaded until the initial set of the polymer. When the substrate temperature is rising, it is recommended to postpone application.

**Minimum application temperature:** Do not apply when substrate temperature is below 50°F.

For application, the 652 Topcoat resin & hardener should be stored at a minimum temperature of 70°F. Always apply the material as soon as blended. The pot life is approximately 25 minutes, and the working life is approximately 40 minutes.

**APPLICATION - 652 Topcoat can be applied by spray, brush, or roller. Two coats recommended for immersion applications, at 7-10 mils per coat.**

**Spray:** Use a Graco King 45 to 1 type, hydrospray pump, Model 208-311. High pressure 3/4" inside diameter nylon hose not to exceed 25 feet. All hoses rates 6000 psi. Inlet pressure to the pump shall be 100 psi.

**Brush:** A high quality natural bristle brush should be used.

**Roller:** Use a 3/8" nap roller with phenolic core.

**CURE TIME** - Will harden in approximately 8-12 hours at 75°F. The warmer the temperature, the faster the cure. Allow 24 hours, at 75°F, for light traffic, and 96 hours for full cure.

Minimum recoat times are as follows: 12 hours at 60°F, 4 hours at 75°F, 2 hours at 90°F

**CLEAN-UP** - Cured or hardened 652 is almost impossible to remove. Clean tools and equipment immediately with hot soapy water, or a mixture a acetone and ethanol.

### SAFETY

Observe good personal hygiene. Certain personnel may be sensitive to various types of resins which may cause dermatitis. Avoid contact with skin and breathing of vapor. Read and follow all caution statements on product info bulletin, material safety data sheet and container labels for this product. This bulletin provides standard information for the system and application procedure. Since varying application conditions may not be covered, consult GREENSTONE Technical Service Department for further information.