

1 = Long Term Exposure (500 Hours Minimum)
2 = Short Term Exposure (Less Than 72 Hours)

3 = Splash And Spill (Less Than 8 Hours)
4 = Not Recommended For Direct Contact

Blank Box = No Test Data Available - Check with Greenstone
Technical Service for specific product recommendation.

* Double Veil Coat Recommended

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Acetaldehyde	20.0%	75										2		1										1	2	1	2		1
Acetaldehyde		75			2				2			3		2			2	2			2	2		2	3	2	3		2
Acetic Acid	5.0%	75					1	1	1			1		1				1		1	1	1	2	1	2	1	2		1
Acetic Acid	5.0%	100					1	1	1			1		1				1		1	1	1	2	2	2	2	2		2
Acetic Acid	5.0%	120							2			1		1				2			2		2	2	2	2	2		2
Acetic Acid	5.0%	150										2		1									2	2	2	2	2		2
Acetic Acid	10.0%	75		2	2	2	2	2	2	3	1	1	1	1		2	2	2	2	2	2	2	1	1	2	1	2	1	1
Acetic Acid	10.0%	150			2				2			2	1	1			2	2		2	2	2		2	2	2	2	2	2
Acetic Acid	20.0%	75		3	2	3	3	3	2		2	1	1	1		3	2	2	3	3	2	2	1	1	1	1	1	1	1
Acetic Acid	20.0%	150			2				2			2	2	1			2			3	2				2	1	2	2	1
Acetic Acid	30.0%	75		3	2	3	3	3	2		2	1	1	1		3	2	2	3	3	2	2			1	1	1	1	1
Acetic Acid	30.0%	120										1	1	1									1	1	1	1	1		1
Acetic Acid	50.0%	75		3	3				3			1	1	1			3	2	4	3	3	2	1		1	1	1		1
Acetic Acid	50.0%	120										1		1									1	1					
Acetic Acid	75.0%	75										2		1										1	2	1	2		1
Acetic Acid	85.0%	75										3	3	1											3	1	3	3	1
Acetic Acid	Glacial	75		4	3	4	4	4	3		4	3	3	1		4	3	2	4	4	3	2	3	1	4	2	3	3	1
Acetic Acid	Glacial	100																					3	1		2			1
Acetic Acid (Pickle Brine)	4.0%	75		2	1			2	1		2	1	1	1			1		2		1				1	1	1	1	1
Acetic Acid (Vinegar)	6.0%	75			1				1			1					1				1				1		1		
Acetic Acid 20%, Sulfuric Acid 10%		100										1		1											1	1	1		1
Acetic Anhydride		75		3	2	3	3	3	2			2	1	1		3	2	2	3	3	2	2			2	1	2	1	1
Acetone		75		3	3	3			3	3		4	4	4		3	3	3	3	3	3	3			4	4	4	4	4
Acetone	10.0%	100												2												2			2
Acetonitrile		75			3		4	4	3			4		2			3	3			3	3			4	2	4		2
Acetophenone		75			3		4	4	3		4	4		2			3	3			3	3			4	2	4		2
Acetyl Acetone	20.0%	75										2		1											2	1	2		1
Acetyl Acetone		75										3		2											3	2	3		2

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Acetyl Bromide		75			2				2							2	2				2	2	4	4		4	4		4
Acetyl Chloride		75			2				2							2	2				2	2	4	3					
Acetylene Tetrachloride		75							1					1			1					1		1		1			1
Acrylaldehyde (Acrolein)	20.0%	75										2		1									2	1	2	1	2		1
Acrylaldehyde (Acrolein)		75										3		2									3	2	3	2	3		2
Acrylamide	50.0%	75										2	2	1												1		2	2
Acrylamide		75										2	2	2												2		2	
Acrylic Acid	5.0%	75										1	1	1									1	1	1	1	1	1	1
Acrylic Acid	5.0%	150																					2	1					
Acrylic Acid	20.0%	75			3				3			2	1	1			3	3			3	3	1	1	2	1	2	1	1
Acrylic Acid	20.0%	150																					2	2					
Acrylic Acid	50.0%	75								3		3		1									2	2	3	2	3		2
Acrylic Acid	60.0%	100																					2	3					
Acrylic Acid	60.0%	150																					2	3					
Acrylic Acid	80.0%	100																					2	2					
Acrylic Acid	80.0%	150																					2	2					
Acrylic Acid	Esterfied	75												1					2					1		1			1
Acrylic Acid	Glacial	75			3				3			2	2	1			3	3		3	3	3	2	1	2	1	2	2	1
Acrylic Acid	Glacial	150																					3	2					2
Acrylonitrile	5.0%	75										1		1									1	1	1	1	1		1
Acrylonitrile	20.0%	75										2		1											2	1	2		1
Acrylonitrile		75		3	2		3	3	3		4	3	3	2		3	2	2	3	2	2	2	3	2	3	2	3	3	2
Acrylonitrile		100																					3	2					
Activated Carbon (Slurry)		75										1		1									1	1	1	1	1		1
Activated Carbon (Slurry)		150										1		1									1	1	1	1	1		1
Adipic Acid	Sat.	75			1		1	1	1		2	2		1			1	1		1			1	1	2	1	2		1
Adipic Acid		120																						1					
Adiponitrile		75										1		1									1	1	1	1	1		1
Alcohol Ethoxy Sulfates		120																					1	1					
Alkyl Aryl Sulfonic Acid	91.0%	100										1		1									1	1	1	1	1		1
Alkyl Benzene	Linear	100															1				1								
Alkyl Benzene Sulfonic Acid		100										1	1	1									1	1	1	1	1	1	1
Alkyl Benzene Sulfonic Acid		150																					1	1					

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Alkyl Chloride (C8-C18)	0.5%	100										1		1											1	1	1		1
Alkyl Dimethyl Amine (C8-C10)		100										1		1											1	1	1		1
Alkyl Glycidyl Ether (C8-C10)		100										2		1											2	1	2		1
Alkyl Glycidyl Ether (C8-C10)		150										2		1									2	1	2	1	2		1
Alkyl Glycidyl Ether Sulfonate 58%:NaCl 2%		150										1		1									1	1	1	1	1		1
Alkyl Glycidyl Ether Sulfonate 58%:NaCl 2%		200										2		1									2	1	2	1	2		1
Alkyl Toly Trimethyl Ammonium Chloride		100										2		1											2	1	2		1
Allyl Alcohol		75										3		2											3	2	3		2
Allyl Chloride		75										3		2									3	2	3	2	3		2
Alpha Methylstyrene		75										2		1											2	1	2		1
Alpha Oleum Sulfates		100										1		1											1	1	1		1
Alum	Sat.	100										1	1	1											1	1	1	1	1
Alumina Hydrate		100										1		1											1	1	1		1
Aluminum Ammonium Sulfate	50.0%	100			1							1					1			1	1				1		1		
Aluminum Ammonium Sulfate	50.0%	150																					2	1					
Aluminum Chloride	5.0%	75					1	1	1		1	1	1	1						1			1	1	1	1	1	1	1
Aluminum Chloride	15.0%	120										1	1	1									1	1	1	1	1	1	1
Aluminum Chloride	25.0%	75					1	1	1		1	1	1	1						1			1	1	1	1	1	1	1
Aluminum Chloride	29.0%	150										1	1	1									1	1	1	1	1	1	1
Aluminum Chloride	32.0%	100																					1	1					
Aluminum Chloride	32.0%	100																					1	1					
Aluminum Chloride	32.0%	210										2	2	2										2	2	2	2	2	2
Aluminum Chloride	Sat.	100										1		1											1	1	1		1
Aluminum Chlorohydrate	50.0%	100										1	1	1											1	1	1	1	1
Aluminum Chlorohydrate		100										1		1											1	1	1		1
Aluminum Chlorohydroxide	50.0%	100										1		1											1	1	1		1

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Aluminum Citrate	Sat.	100										1		1											1	1	1		1
Aluminum Fluoride	1.0%	100					1	1												1						1			1
Aluminum Fluoride	5.0%	100					1	1				2	2	1						1			1	1	2	1	2	2	1
Aluminum Fluoride	5.0%	150												1								1	1		1				1
Aluminum Fluoride	10.0%	100					1	1				2	2	1						1			1	1	2	1	2	2	1
Aluminum Fluoride	20.0%	100					1	1				2	2	1						1			1	1	2	1	2	2	1
Aluminum Fluoride	Sat.	100																				1	1						
Aluminum Hydroxide	20.0%	75										1		1											1	1	1		1
Aluminum Hydroxide	Sat.	75										1		1								1	1	1	1	1	1		1
Aluminum Hydroxide	Sat.	120																				1	1						
Aluminum Nitrate	50.0%	75			1		1	1	1		2	1		1			1	1		1	1	1	1	1	1	1	1		1
Aluminum Nitrate	50.0%	150										1		1								1	1	1	1	1	1		1
Aluminum Nitrate	80.0%	75										1		1			1				1			1	1	1		1	
Aluminum Nitrate	Sat.	75										1		1										1	1	1		1	
Aluminum Potassium Sulfate	Sat.	75			1		1	1	1		2	1	1	1			1	1		1	1	1	1	1	1	1	1	1	1
Aluminum Potassium Sulfate	Sat.	75																				1	1						
Aluminum Sulfate	5.0%	75					1	1	1		2	1	1	1				1		1		1	1	1	1	1	1	1	1
Aluminum Sulfate	8.0%	150			1							1	1	1			1	1		1	1	1	2	1	1	1	1	1	1
Aluminum Sulfate	10.0%	100																				1	1						
Aluminum Sulfate	10.0%	120																				1	1						
Aluminum Sulfate	30.0%	100										1		1				1			1			1	1	1		1	
Aluminum Sulfate	50.0%	100																				1	1						
Aluminum Sulfate	50.0%	150			1							2	2	1			1	1		1	1	1	2	1	2	1	2	2	1
Aluminum Sulfate	Sat.	100										1		1										1	1	1		1	
Ammonia (dry)	Gas	75																						1	1	1	2	1	
Ammonia (wet)	Gas	75																						1	2	1	3	2	
Ammonia Anhydrous		75			1				1								1				1					1			
Ammonium Acetate	0.5%	75										2		1										2	1	2		1	
Ammonium Acetate	50.0%	75										2		2										2	2	2		2	
Ammonium Bicarbonate	10.0%	75										1		1										1	1	1		1	
Ammonium Bicarbonate	25.0%	75										1	1	1										1	1	1	1	1	
Ammonium Bicarbonate	Sat.	75										1	1	1										1	1	1	1	1	
Ammonium Bifluoride	12.0%	75			1		1	1	1			1		1			1	1		1	1	1		1	1	1		1	

			* Double Veil Coat Recommended																											
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662	
Ammonium Bifluoride		75										1		1											1	1	1		1	
Ammonium Bisulfide		100										1		1			1				1	1	1	1	1	1	1		1	
Ammonium Bisulfite		100																					1	1	1	1	1		1	
Ammonium Bromate		100										1		1											1	1	1		1	
Ammonium Bromide	40.0%	100										1		1											1	1	1		1	
Ammonium Bromide	Sat.	75										1		1											1	1	1		1	
Ammonium Bisulfide		100										1		1			1				1				1	1	1		1	
Ammonium Carbonate	30.0%	75										2	2	1											2	1	2	2	1	
Ammonium Carbonate	Sat.	75										1	1	1											1	1	1	1	1	
Ammonium Chloride	50.0%	100					1	1				1	1	1						1					1	1	1	1	1	
Ammonium Chloride	Sat.	75					2	2	2		2	1	1	1											1	1	1	1	1	
Ammonium Citrate	Sat.	75										1		1											1	1	1		1	
Ammonium Fluoride	Sat.	75										2	1	1			1				1				2	1	2	1	1	
Ammonium Hydroxide	5.0%	100		1			1	1	1			1		1		1			1	1	1	1	2	2	2	2	2		2	
Ammonium Hydroxide	10.0%	75		2								1	2	1			1				1	1	1	1	1	1	1	2	1	
Ammonium Hydroxide	10.0%	100																												
Ammonium Hydroxide	20.0%	100										1	2	2									1	2	1	2	1	2	2	
Ammonium Hydroxide	24.7%	75																						1	2					
Ammonium Hydroxide	29.0%	75		2	1	2	1	1	1		2	1	3	2		2	1	1	2	1	1	1	1	2	1	2	1	3	2	
Ammonium Hydroxide	29.0%	120																					2	2						
Ammonium Hydroxide	29.0%	150																					2	2						
Ammonium Lauryl Sulfate	30.0%	75										1		1									1	1	1	1	1		1	
Ammonium Lauryl Sulfate		120																					1	1						
Ammonium Lignin Sulfonate	52.0%	150										1		1				2					1	1	1	1	1		1	
Ammonium Molybdate		100										1													1		1			
Ammonium Nitrate		120																					1	1						
Ammonium Nitrate	5.0%	75		1		1						1	1	1		2									1	1	1	1	1	
Ammonium Nitrate	50.0%	75			1		1	1	1		2	1	1	1			1	1	2	1	1	1	1	1	1	1	1	1	1	
Ammonium Nitrate	50.0%	130										1		1									1	1	1	1	1		1	
Ammonium Nitrate	83.0%	250																						1						
Ammonium Nitrate	Sat.	75										1	1	1											1	1	1	1	1	
Ammonium Oxylate		100										1													1		1			

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Ammonium Pentaborate	12.0%	75										1											1	1	1	1	1		1
Ammonium Pentaborate	12.0%	150																					2	1					
Ammonium Perchlorate	10.0%	150										2		1											2	1	2		1
Ammonium Persulfate	10.0%	100					1	1				1	1	1				1		1		1	1	1	1	1	1	1	1
Ammonium Persulfate	10.0%	150			1							2	2	1			1	2		2	1	2	2	1	2	1	2	2	1
Ammonium Persulfate	Sat.	100										1	1	1										1	1	1	1	1	1
Ammonium Persulfate	Sat.	120																						1					
Ammonium Phosphate (Monobasic)	50.0%	75					1	1			1	1	1	1						1					1	1	1	1	1
Ammonium Polysulfide	Sat.	100										2		1											2	1	2		1
Ammonium Sulfate	46.0%	150										1	1	1						1					1	1	1	1	1
Ammonium Sulfate	50.0%	75					1	1	1			1	1	1											1	1	1	1	1
Ammonium Sulfate	Sat.	100										1	1	1											1	1	1	1	1
Ammonium Sulfate	Sat.	120																					1						
Ammonium Sulfate	8.0%	100																					1						
Ammonium Sulfate	8.0%	150																					2	1					
Ammonium Sulfide (Bisulfide)	25.0%	100										1	1	1											1	1	1	1	1
Ammonium Sulfide (Bisulfide)	45.0%	150										2		2									2	2	2	2	2		2
Ammonium Sulfide (Bisulfide)	Sat.	100										1		1									1	1	1	1	1		1
Ammonium Sulfide (Bisulfide)	Sat.	120																						1					
Ammonium Sulfide (Bisulfide)	Sat.	150																					2	1					
Ammonium Sulfite	10.0%	100										2		1											2	1	2		1
Ammonium Sulfite	Sat.	100										1		1									1	1	1	1	1		1
Ammonium Thiocyanate	20.0%	100										1	1	1											1	1	1	1	1
Ammonium Thiocyanate	Sat.	100										2	1	2											2	2	2	1	2
Ammonium Thioglycolate	7.5%	100										2													2		2		
Ammonium Thioglycolate		100										2		2											2	2	2		2
Ammonium Thiosulfate	60.0%	75										1		1									1		1	1	1		1

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Ammonium Thiosulfate		75										1		1									1	1	1	1	1		1
Ammonium Xylene Sulfonate 40%, Ammonium Sulfate 2%		100																					1	1					
Ammonium Xylene Sulfonate 40%, Ammonium Sulfate 2%		100																					2	2					
Ammonium Xylene Sulfonate 40%, Ammonium Sulfate 2%		100																					2	2					
Amyl Acetate	10.0%	75										2		1											2	1	2		1
Amyl Acetate		75										3	2	1				1				1	2	1	2	1	2	2	1
Amyl Alcohol		100										2	1	1				1				1		1	2	1	2	1	1
Amyl Chloride		75										2	2	1											2	1	2	2	1
Aniline		75																						1					
Aniline		100							3			3	3	2				2				2	2	2	3	2	3	3	2
Aniline Hydrochloride		75				1	1				2	1		1				1		1		1	1	1	1	1	1		1
Aniline Sulfate		100										1	1	1											1	1	1	1	1
Antimony Pentachloride		75										2	2	2											2	2	2	2	2
Antimony Trichloride	Sat.	100										1	1	1				1				1	1	1	1	1	1	1	1
Aqua Regia		75			2				2			3		3			2	2			2	2			3	3	3		3
Aromatic 100		75			1		1	1	1		2	1		1			1	1		1	1	1			1	1	1		1
Arsenic Acid	75.0%	75																					1	1					
Arsenic Acid	75.0%	75										1		1									1	1	1	1	1		1
Arsenic Trioxide		100										1		1				2				2			1	1	1		1
Aviation Fuel		75			1				1			1	1	1			1	1			1	1			1		1		
Azelaic Acid	Sat.	100											2															2	
Barium Acetate		100										1	1	1											1	1	1	1	1
Barium Bromide	Sat.	100										1		1											1	1	1		1
Barium Carbonate	Slurry	100										1		1											1	1	1		1
Barium Chloride	Sat.	100										1		1				1				1			1	1	1		1
Barium Cyanide		100										1		1											1	1	1		1
Barium Hydroxide	10.0%	100										1		1											1	1	1		1
Barium Hydroxide	Sat.	100										1		1				1				1			1	1	1		1
Barium Nitrate	50.0%	150										1		1										1	1	1	1	1	1

* Double Veil Coat Recommended																														
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662	
Barium Sulfate	All	100										1	1	1			1					1		1	1	1	1	1	1	1
Barium Sulfide	20.0%	120										1		1								1	1	1	1	1			1	
Barium Sulfide	Sat.	100										1		1			1				1			1	1	1			1	
Beer		75			1				1			1	1	1		1	1				1	1			1	1	1	1	1	
Benzyl Dichloride		75										2		1			1				1			2	1	2			1	
Benzaldehyde		75					4	4			4	3	4	2			2				2	3	2	3	2	3	4		2	
Benzalkonium Chloride		75										2		2										2	2	2			2	
Benzene		75		2	3	2	3	3	3		4	3	2	1		3	3	1	2	1	3	1		1	3	1	3	2	1	
Benzene		100												2									2		2				2	
Benzene 33%, Ethylbenzene 67%		75												1												1			1	
Benzene 50%, Gasoline 45%, MTBE 5%		100												1									1		1				1	
Benzene 50%, Gasoline 50%		100												1			1				1		1		1				1	
Benzene 80%, MTBE 20%		75												1												1			1	
Benzene Sulfonic Acid	30.0%	100										1	1	1											1	1	1	1	1	
Benzene Sulfonic Acid		100										1	2	1			2				2	1	1	1	1	1	1	2	1	
Benzene Sulfonyl Chloride		75					2	2				2		2					2				2	2	2	2	2		2	
Benzoic Acid	Sat.	100										1	1	1			1				1			1	1	1	1	1	1	
Benzoic Anhydride		75										1																1		
Benzoyl Benzoic Acid		100										1		1										1	1	1			1	
Benzoyl Chloride		75										4	4	2			2				2	2	2	2	4	2	4	4	2	
Benzoyl Chloride		120																					2							
Benzyl Alcohol	20.0%	75										2		1								2	1	2	1	2			1	
Benzyl Alcohol		75										2		1			2				2	2	2	2	2	2			2	
Benzyl Alcohol		120																				3	2							
Benzyl Chloride		75										4	4	2			2				2	4	2	4	2	4	4	4	2	
Benzyl Peroxide		100					1	1				1		1					1				1	1	1	1	1		1	
Benzyl Peroxide 10%, Sodium Hydroxide 5%		75					1	1				1		2			1		1		1			1	2	1			2	
Benzyl Trimethyl Ammonium Chloride	60.0%	75										1		1										1	1	1			1	

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Boric Acid	5.0%	75			1		1	1	1			1		1			1	1		1	1	1	1	1	1	1			1
Boric Acid	25.0%	75					2	2	2		2	1	1	1				1		1	1	1	1	1	1	1	1	1	1
Boric Acid	Sat.	100										1	1	1				1			1	1	1	1	1	1	1	1	1
Bromine (gas)		75												1												1			1
Bromine (liquid)		75										3	3	3											3	3	3	3	3
Butane		100										1		1											1	1	1		1
Butoxyethanol	20.0%	75										2		1											2	1	2		1
Butoxyethanol		75										2		1											2	1	2		1
Butoxyethoxyethanol		75										1		1											1	1	1		1
Butyl Acetate - N		75		2		2				2		3	2	1		2							3	1	3	1	3	2	1
Butyl Acrylate		75										2		1				1				1	2	1	2	1	2		1
Butyl Alcohol - N		75		3		3						2	2	1		3		1	1			1	2	1	2	1	2	2	1
Butyl Alcohol 93%, Benzene 4%		75										2		1											2	1	2		1
Butyl Amine		75										3		2											3	2	3		2
Butyl Benzoate		75												1												1			1
Butyl Benzyl Phthalate		100										1		1											1	1	1		1
Butyl Carbitol		100										2	2	1				2				2	3	1	3	1	3	2	1
Butyl Carbitol Acetate		75										3		2				1				1	3	2	3	2	3		2
Butyl Carbitol diethylene glycol		75										2		1											2	1	2		1
Butyl Cellosolve		75										2	2	1				1				1	2	1	2	1	2	2	1
Butyl Cellosolve Acetate		75										3		1				1				1			3	1	3		1
Butyl Chloride		75										3		2											3	2	3		2
Butyl Ether		75										2	2	2				2				2	3	2	3	2	3	2	2
Butyl Glycidyl Ether		75										3		1									3	1	3	1	3		1
Butyl Hypochlorite		75										3		3											3	3	3		3
Butyl Levuline Acid		75										3		2				2				2	3	2	3	2	3		2
Butyl Methyl Ether		100										2		1											2	1	2		1
Butylamine		75										3		2				2				2	3	2	3	2	3		2
Butylene		75			1				1			2				1					1				2		2		
Butylene Glycol		100										1	1	1									1	1	1	1	1	1	1
Butylene Glycol		150										2		1									1	1	2	1	2		1
Butylene Oxide		75										3		2											3	2	3		2

* Double Veil Coat Recommended																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																
--------------------------------	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Caproic Acid	98.0%	100										2		1									3	1	2	1	2		1
Caproic Acid	98.0%	150										3		2									3	1	3	2	3		2
Caprolactam	50.0%	75										2		1									2	1	2	1	2		1
Caprolactam		75										3		2									3	2	3	2	3		2
Caprylic Acid	5.0%	100										1	1	1									1	1	1	1	1	1	1
Caprylic Acid		100										1	1	1									1	1	1	1	1	1	1
Carbolic Acid		100										3		1			2				2	2	3	1	3	1	3		1
Carbon Disulfide		75						2				2		1			1		2	2	1	1	1	1	1	1	1		1
Carbon Disulfide		100																					2	1					
Carbon Tetrachloride		75										2	1	1			1				1	1	2	1	2	1	2	1	1
Carbon Tetrachloride 90%, Chloroform 10%		75												1									1		1				1
Carbonic Acid	Sat.	100										2	1											2		2	1		
Carboxyethyl Cellulose	10.0%	75										1		1										1	1	1		1	
Castor Oil		100										1		1			1				1		1	1	1	1		1	
Cellosolve		100										1		1			1				1	1		1	1	1		1	
Cellosolve Acetate		100										3		1			1				1		1	3	1	3		1	
Cetyl Alcohol (Hexadecanol)		100										1		1										1	1	1		1	
Chlorendic Anhydride	66.0%	100										1																1	
Chloric Acid		75										2		2										2	2	2		2	
Chlorine Dioxide	12.0%	75			2			2				2		1		2							2	1	2	1	2		1
Chloroacetic Acid (MCA)	5.0%	75										1		1									1	1	1	1	1		1
Chloroacetic Acid (MCA)	25.0%	75										1	2	1									1	1	1	1	1	2	1
Chloroacetic Acid (MCA)	50.0%	75										2	2	2									2	2	2	2	2	2	2
Chloroacetic Acid (MCA)	80.0%	75			3		4	4	3		2	3		2		3			3	3			3	2	3	2	3		2
Chloroacetic Acid (MCA)		75										3		2									3	2	3	2	3		2
Chlorobenzene		75										3		1			2				2	2	3	1	3	1	3		1
Chlorobutane		100										1		1			1				1	1	1		1	1	1		1
Chlorodimeform		100										2		1										2	1	2		1	
Chloroform		75										3		2			2				2	2	3	2	3	2	3		2
Chloropentane		75										2		1										2	1	2		1	
Chlorophenol		100										3		3			2				2	4	3	4	3	4		3	
Chloropicrin		100										3		2										3	2	3		2	
Chloropyridine (tetra)		75										3		1			1				1			3	1	3		1	

			* Double Veil Coat Recommended																											
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662	
Chlorosulfonic Acid		100										3		3				2				2			3	3	3		3	
Chlorothene	99.0%	100											4	2						3						2		4	2	
Chlorotoluene		75										2		2				1				1			2	2	2		2	
Chlorotriethylamine		120										1		1									1	1	1	1	1		1	
Chromated Copper Arsenate	3.0%	75		1		1	1	1			1	1		1		1		1		1		1		1	1	1	1		1	
Chromated Copper Arsenate	4.0%	75		1		1	1	1			1			1		1		1		1		1		1		1			1	
Chromated Copper Arsenate	4.0%	150					1	1			1			1				1		1		1		1		1			1	
Chromated Copper Arsenate	10.0%	75		1		1	1	1			1			1		1		1		1		1		1		1			1	
Chromated Copper Arsenate	10.0%	150					1	1			1			1				1		1		1		1		1			1	
Chromated Copper Arsenate	50.0%	75		1		1	1	1			1			1		1		1		1		1		1		1			1	
Chromic Acid	1.0%	75			1		1	1	1		2	1	1	1			1	1		1	1	1	1	1	1	1	1	1	1	
Chromic Acid	5.0%	100										2	1	1						1			1	1	2	1	2	1	1	
Chromic Acid	10.0%	75			1		1	1	1		2	1	1	1			1	1	2	1	1	1	1	1	1	1	1	1	1	
Chromic Acid	10.0%	150										2	1	1				1		2		1		1		1		1	1	
Chromic Acid	20.0%	75			2		3	3	3			3	1	1			2			2	2		3	1	3	1	3	1	1	
Chromic Acid	20.0%	100			3				3			3	1	2			3			3	3			2	3	2	3	1	2	
Chromic Acid	20.0%	150										3	2	2					3					2	3	2	3	2	2	
Chromic Acid	30.0%	75										3		2										2	3	2	3		2	
Chromic Acid	40.0%	75										3	2	2				2				2		2	3	2	3	2	2	
Chromic Acid	50.0%	75		3	3	3	3	3	3		3	4	2	2		3	3	2	3	2	3	2		2	4	2	4	2	2	
Chromic Acid	Sat.	75											2	3									3		3		2	3		
Chromic Chloride	Sat.	100										1		1				1				1	1	1	1	1	1		1	
Chromic Chloride		120																						1						
Chromic Sulfate	40.0%	100										1		1				1				1	1	1	1	1	1		1	
Chromium Sulfate	Sat.	100										1		1											1	1	1		1	
Citric Acid	5.0%	100										1		1				1				1	1	1	1	1	1		1	
Citric Acid	5.0%	120																					1	1						
Citric Acid	20.0%	75		2	1	2	2	2	1	2	1	1	1	1		2	1		2	2	1		1	1	1	1	1	1	1	
Citric Acid	50.0%	75		2	2	2	2	2	2		2	1	1	1		2	2	2	2	2	2	2			1	1	1	1	1	

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Citric Acid	50.0%	150																					1	1					
Citric Acid		100																					1	1					
Citric Acid		120																						1					
Cobalt Acetate	40.0%	150										1		1									1	1	1	1	1		1
Cobalt Citrate	12.0%	100										1		1										1	1	1		1	
Cobalt Nitrate	Sat.	100										1	2	2										1	2	1	2	2	
Copper Acetate	Sat.	100										1		1										1	1	1		1	
Copper Chloride	Sat.	100										1		1			1				1			1	1	1		1	
Copper Cyanide	Sat.	100										1		1			1				1			1	1	1		1	
Copper Cyanide 7%, Potassium Cyanide 2.5%, Potassium Hydroxide 2%		100										1		2										1	2	1		2	
Copper Nitrate	Sat.	100										1		1			1				1			1	1	1		1	
Copper Sulfate	50.0%	150		1								1	1	1		1	1		1	1	1			1	1	1	1	1	
Copper Sulfate	Sat.	75				1	1	1		2	1	1	1				1		1	1	1			1	1	1	1	1	
Copper Sulfate	Sat.	100				1	1										1		1		1			1	1	1		1	
Corn Oil		100				1	1	1		1	1	1	1				1		1	1	1	1	1	1	1	1	1	1	
Corn Syrup		100		1		1	1	1				1		1		1	1		1	1	1	1	1	1	1	1		1	
Cottonseed Oil		100										1		1			1				1	1	1	1	1	1		1	
Creosote Oil		75		2		1	1	2								2	1			2	1								
Cresol		75							3			3		2			2				2		2		2			2	
Cresylic Acid		100		3								3	3	2		3	2		3	3	2	3	2	3	2	3	3	2	
Cresylic Acid		150																				4	2						
Cumene		100										2		1			1				1	2	1	2	1	2		1	
Cupric Ammonium Chloride		100										1		1			1				1			1	1	1		1	
Cupric Chloride	5.0%	100										1		1									1	1	1	1	1	1	
Cupric Chloride	5.0%	150										1		1									1	1	1	1	1	1	
Cupric Chloride	20.0%	100										1		1									1	1	1	1	1	1	
Cupric Chloride	20.0%	150										1		1									1	1	1	1	1	1	
Cupric Chloride	50.0%	100										1		1									1	1	1	1	1	1	
Cupric Chloride	50.0%	150										1		1									1	1	1	1	1	1	
Cupric Chloride	Sat.	100												2										2		2		2	
Cupric Chloride	Sat.	150												2											2			2	

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Cyanuric Acid		75										2		1											2	1	2		1
Cyanuric Chloride		100										1		1										1	1	1		1	
Cyclohexane		75			1		1	1	1		2	1	1	1			1	1		1	1	1	1	1	1	1	1	1	1
Cyclohexane		100										2	1	1									2	1	2	1	2	1	1
Cyclohexanol		100										2		1			1					1	2	1	2	1	2		1
Cyclohexanone		100										1		1			1					1			1	1	1		1
Cyclohexene		100										1		1									1	1	1	1	1		1
Cyclohexylamine		75										3		2									3	2	3	2	3		2
Cyclopentane		75										2		1											2	1	2		1
Cymene		100										2		1			1					1			2	1	2		1
Decanoic Acid		100										2		2											2	1	2		2
Decanol		100										2		1											2	1	2		1
Diacetone Alcohol	10.0%	75												1												1			1
Diacetone Alcohol		75										3		2											3	2	3		2
Diallyl Phthalate		100										1		1											1	1	1		1
Dibromo-(1,2) dichloroethane-(1,1)		100										3		1									3	1	3	1	3		1
Dibromoethane-(1,2)		100										3		2									3	2	3	2	3		2
Dibromonitrilo- Propionamide		75										2		1											2	1	2		1
Dibromophenol		75										3	2	2											3	2	3	2	2
Dibromopropanol		75												1												1			1
Dibromopropane		75										2		1											2	1	2		1
Dibutyl Carbitol (diethylene glycol dibutyl ether)		75										2		1											2	1	2		1
Dibutyl Ether		75										2	2	1											2	1	2	2	1
Dibutyl Phthalate		100										1	2	1			1					1			1	1	1	2	1
Dibutyl Sebacate		75										1		1											1	1	1		1
Dichloroacetic Acid		100										1		1			2					2			1	1	1		1
Dichlorobenzene		75										3	3	1			1					1			3	1	3	3	1
Dichloroethane (1,2)		75										3	3	2											3	2	3	3	2
Dichloroethylene		75										3		2											3	2	3		2
Dichloromethane (Methylene Chloride)		75			3		4	4	3	4	4	4	4	3			3		4	4	3				4	3	4	4	3

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Dichlorophenoxyacetic Acid (2,4)		75										1		1											1	1	1		1
Dichloropropane		75										3		1											3	1	3		1
Dichloropropene		75										3		1											3	1	3		1
Dichloropropionic Acid		75										3		1											3	1	3		1
Dichlorotoluene		75										2		1									2	2	2	2	2		2
Diesel Fuel		75		1	1	1		1	1			1	1	1		1	1	1	1	1	1	1	1	1	1	1	1	1	1
Diethanolamine	30.0%	75										2	2	1											2	2	2	2	2
Diethanolamine	50.0%	120										1		1				1				1			2	2	2		2
Diethanolamine		75		2	1	2	2	2	1		2	2	2	2		2	1	2	2	3	1	2	1	1	2	2	1	2	1
Diethanolamine		100			2				2			2	2	2			2				2		2	1	2	2	1	2	1
Diethanolamine		150										2		2									2	2	2	2	2		2
Diethyl Benzene		75										2	1	1									2	1	2	1	2	1	1
Diethyl Carbonate		75										3		1											3	1	3		1
Dimethyl Disulfide	1.0%	100										1		1									1	1			1		1
Diethyl Ether		75										3		2				2				2	3	2	3	2	3		2
Diethyl Formamide	20.0%	75										1		1											1	1	1		1
Diethyl Formamide		75										3		1											3	1	3		1
Diethyl Glycol		75										1		1											1	1	1		1
Diethyl Hydroxamide		75										3		2											3	2	3		2
Diethyl Ketone	20.0%	75										1		1											1	1	1		1
Diethyl Ketone		75										3		2											3	2	3		2
Diethyl Sulfate		75										2	2	1											2	1	2	2	1
Diethylamine	20.0%	75										1		1											1	1	1		1
Diethylamine		75			2				2			3		2			2	2			2	2			3	2	3		2
Diethylaminoethyl Chloride		100										1		1											1	1	1		1
Diethylaminoethyl Chloride		150										2		2											2	2	2		2
Diethylaminopropylamine		75										3		2				2				2			3	2	3		2
Diethylbenzene		75										2		1				1				1			2	1	2		1
Diethylene Glycol		100										1	1	1											1	1	1	1	1
Diethylene Glycol Butyl Ether		75										2		1											2	1	2		1

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Diethylenetriamine		75			2		3	3	2		4	4	4	3			2	2		3	2	3			4	3	4	4	3
Diethylenetriaminepentaacetic Acid		75										2		1										2	1	2		1	
Diethylketone		75															1				1								
Diglycolamine	20.0%	75										2		1								1			2	1	2		1
Diglycolamine	50.0%	75										2		2										2	2	2		2	
Diglycolamine		75										3		2										3	2	3		2	
Diisobutyl Ketone		75										3		1										3	1	3		1	
Diisobutyl Phthalate		75										2	2	1										2	1	2	2	1	
Diisobutylene		75										2	1	1										2	1	2	1	1	
Diisonoyl Phthalate		100										1		1										1	1	1		1	
Diisopropanolamine		100										2		1										2	1	2		1	
Dimethyl Acetamide	20.0%	75										1		1										1	1	1		1	
Dimethyl Acetamide		75										3		2								3	2	3	2	3		2	
Dimethyl Amine	20.0%	75										2		2								2	2	2	2	2		2	
Dimethyl Amine	40.0%	75										2		2										2	2	2		2	
Dimethyl Aniline		75										3		1									2	3	2	3		2	
Dimethylaminopropylamine		100												2									2					2	
Dimethyl Disulfide	1.0%	100										1		1								1	1	1	1	1		1	
Dimethyl Disulfide	1.0%	150										2		1								2	1	2	1	2		1	
Dimethyl Disulfide	5.0%	100										1		1								1	1	1	1	1		1	
Dimethyl Disulfide	5.0%	150										2		1								2	1	2	1	2		1	
Dimethyl Disulfide		75						3		4	2		2				3			3	3	2	2	2	2	2		2	
Dimethylethanolamine		100										3		1								3	1	3	1	3		1	
Dimethyl Formamide	7.2%	75											1	2									2		2		1	2	
Dimethyl Formamide	30.0%	100										2	2	2								3	2	3	2	3	2	2	
Dimethyl Formamide		75			4		4	4	4			4		3		4	3	4	4	4	4	3		3	4	3	4		3
Dimethyl Morpholine		75										3		1										3	1	3		1	
Dimethyl Phthalate		100										1		1										1	1	1		1	
Dimethyl Sulfate	20.0%	75										2		1										2	1	2		1	
Dimethyl Sulfate		75										3		2										3	2	3		2	
Dimethyl Sulfide		75										3		2										3	2	3		2	
Dimethyl Sulfoxide	20.0%	75										1		1										1	1	1		1	
Dimethyl Sulfoxide		75										3		2								3	2	3	2	3		2	

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Dimethyl (2,2) Thiazolidine	1.0%	100										1		1											1	1	1		1
Dimethylacetamide	20.0%	75										1		1											1	1	1		1
Dimethylacetamide	70.0%	75											2															2	
Dimethylacetamide		75							3		4	3	3	2						4	3				3	2	3	3	2
Dimethylamine	4.0%	75											1															1	
Dimethylamine	25.0%	75										2		2											2	2	2		2
Dimethylamine	60.0%	75											2															2	
Dimethylaminoethanol		75										1		1											1	1	1		1
Dimethylaminomethyl - (2,4,6) Phenol		100										1		1											1	1	1		1
Dimethylaniline		75										3		2											3	2	3		2
Dimethylene Glycol Dimethylether	20.0%	75										1		1											1	1	1		1
Dimethylene Glycol Dimethylether		75										3		2											3	2	3		2
Dimethylphenol - (2,4)		150										2		2											2	2	2		2
Dimethylphenol - (2,6)		150										2		2											2	2	2		2
Dimethylsulfoxide		100										3		3											3	2	3		2
Dinitrobenzene		100										4		2				2				2	4	2	4	2	4		2
Dinitrobutylphenol		100										2		2				2				2	2	2			2		2
Dinitrotoluene		100										2		2				2				2	2	2	2		2		2
Diocetyl Phthalate		100										1		1											1	1	1		1
Diphenyl Ether		75										1		1											1	1	1		1
Diphenyl Oxide		75										2		1											2	1	2		1
Dipotassium Phosphate		75										1		1											1	1	1		1
Dipropylene Glycol		100										1		1											1	1	1		1
Dipropylene Glycol Dibenzoate		75										1	1	1											1	1	1	1	1
Dipropylene Glycol Methyl Ether	20.0%	75										2		1											2	1	2		1
Dipropylene Glycol Methyl Ether		75										3		2											3	2	3		2
Disodium Phosphate	Sat.	75																1				1							
Divinyl Benzene		100										2	2	1				1				1			2	1	2	2	1

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Dodecane		100										2	2	1											2	1	2	2	1
Dodecene		100										1		1										1	1	1		1	
Dodecyl Alcohol (Lauryl)		100										1	2	1			1				1			1	1	1	2	1	
Dodecylbenzene		75										3		2										3	2	3		2	
Dodecylbenzene		130										2		2								2	2	2	2	2		2	
Dodecylbenzene Sulfonic Acid		75			2		2	2	2			1		1			2	2		2	2	2	1	1	1	1	1		1
Dodecylbenzene Sulfonic Acid		150										1		1								1	1	1	1	1		1	
Dodecyldimethylamine		100										1		1								1	1			1		1	
Dodecylmercaptan		100										1		1										1	1	1		1	
Epichlorohydrin		75			3		4	4	3		4	3		1			3	2		3	3	2	3	1			3		1
Epichlorohydrin		100																					2						
Ethane		75			1				1			2					1				1			2		2			
Ethanolamine (Monoethanolamine)	10.0%	100			1									1			1	1		1	1	1		1		1			1
Ethanolamine (Monoethanolamine)		75		3	2	3	3	3	2		3	3	2	2		3	2	3	3	3	2	3	3	2			3	3	2
Ethanolamine (Monoethanolamine)		100			2				2			2	3	2		2			2	2	2	4	2			4	3	2	
Ethoxyethanol		100										4		2				1				1	4	2	4	2	4		2
Ethoxylated Nonyl Phenol		100										2		2			2				2	2	2	2	2	2		2	
Ethyl Acetate		75										4	4	2				2	3			2	4	2	4	2	4	4	2
Ethyl Acetoacetate		75											2														2		
Ethyl Acrylate		100										4		2				2				2	4	2			4		2
Ethyl Alcohol	15.0%	100										1		1											1	1	1		1
Ethyl Alcohol	50.0%	100										2	1	1											2	1	2	1	1
Ethyl Alcohol	95.0%	75										2		1											2	1	2		1
Ethyl Alcohol		75		2	2	2	2	2	2		3	3	2	1		2	2	1	2	1	2	1	3	1			3	2	1
Ethyl Alcohol		150			3								4	2			3	2		2	3	2				2		4	2
Ethyl Amine	20.0%	75										1		1											1	1	1		1
Ethyl Amine	70.0%	75										4		3			2				2	4	3			4		3	
Ethyl Bromide		75										4		2			2				2			4	2	4		2	
Ethyl Chloride		75										4	2	2			2				2			3	2	3	2	2	

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Ethyl Chloroformate		75										4	2	2				2				2			4	2	4	2	2
Ethyl Ether		75										4		2				2				2			4	2	4		2
Ethyl Sulfate		75										2	1	1				2				2			2	1	2	1	1
Ethylamine	70.0%	75										3		3									3	3			3		3
Ethylbenzene		75										2	3	1				1				1	2	1			2	3	1
Ethylbenzene		100										3		1									2	1	3	1	3		1
Ethylbenzene		150										4		2											4	2	4		2
Ethylbenzene 67%, Benzene 33%.		75										3		2											3	2	3		2
Ethylene Chloride		75			3				3			3					3				3				3		3		
Ethylene Chlorohydrin	20.0%	100										2		1											2	1	2		1
Ethylene Chlorohydrin		100										2	1	2											2	2	2	1	2
Ethylene Diamine	20.0%	75										1		1											1	1	1		1
Ethylene Diamine		75										3		2											3	2	3		2
Ethylene Dibromide		75										3		2									3	2			3		2
Ethylene Dichloride (Dichloroethane)	1.0%	120										3		2			2				2				3	2	3		2
Ethylene Dichloride (Dichloroethane)		75			3		4	4	3		4	4		2			3	2		4	3	2	4	2	4	2	4		2
Ethylene Dichloride (Dichloroethane)		120										4		2			2				2				4	2	4		2
Ethylene Glycol		75			1		1	1	1		2	1	1	1			1	1	1	1	1	1		1	1	1	1	1	1
Ethylene Glycol		120										1		1			1				1			1	1	1	1		1
Ethylene Glycol		180										1	1	1										1	1	1	1	1	1
Ethylene Glycol	50.0%	150										1		1									1	1	1	1	1		1
Ethylene Glycol Butyl Ether (Butyl Cellosolve)	20.0%	75										1		1										1	1	1	1		1
Ethylene Glycol Butyl Ether (Butyl Cellosolve)		75			1							2	2	1			1	1		1	1	1		1	2	1	2	1	1
Ethylene Glycol Ethyl Ether (Cellosolve)		75			1									1			1	2		2	1	2		1		1			1
Ethylene Glycol Ethyl Ether Acetate (Cellosolve Acetate)		75			1									1			1	1		1	1	1		1		1			1

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Ethylene Glycol Methyl Ether (Methyl Cellosolve)		75			1		2	2						1			1			2	1			1		1			1
Ethylene Oxide		75			3				3			4		2			3	2			3	2	4	2			4		2
Ethylenediamine		75			4		4	4	4		3	3		2			4		4	4	4		3	2			3		2
Ethylenediaminetetraacetic Acid (EDTA)	38.0%	75										2	2	1									2	1			2	2	1
Ethylenediaminetetraacetic Acid (EDTA)		75										2		1									2	1			2		1
Ethyl-Ethoxy Propionate		75										3		2											3	2	3		2
Ethylhexyl Alcohol		75										1		1											1	1	1		1
Ethylhexyl-(2) Acrylate		75										2		2				2			2				2	2	2		2
Ethylhexyl-(p), Dimethylaminobenzoate		100												1										1		1			1
Fatty Acid		120										1		1				1			1				1	1	1		1
Ferric Acetate	Sat.	75										1		1											1	1	1		1
Ferric Chloride	20.0%	100										1		1				1			1				1	1	1		1
Ferric Chloride	40.0%	150										1		1									1	1	1	1	1		1
Ferric Chloride	50.0%	75			1		1	1	1		2	1	1	1			1	1	1	1	1	1	1	1			1	1	1
Ferric Chloride	50.0%	150										2	1	1									2	1			2	1	1
Ferric Chloride	Sat.	100										1	1	1				1			1	1	1	1			1	1	1
Ferric Nitrate		75			1				1			1	1	1			1				1				1	1	1	1	1
Ferric Sulfate	20.0%	120			1							1		1			1				1				1	1	1		1
Ferric Sulfate		75			1				1			1	1	1			1				1				1	1	1	1	1
Ferrous Chloride	40.0%	120			1							1		1			1				1				1	1	1		1
Ferrous Chloride	Sat.	100										1	1	1											1	1	1	1	1
Ferrous Chloride 20%, Ferric Chloride 5%		100										1	1	1											1	1	1		1
Ferrous Nitrate	Sat.	120			1							1	1	1			1				1				1	1	1	1	1
Ferrous Sulfate	Sat.	100										1	1	1											1	1	1	1	1
Flue Gas, Dry		325										1		1											1	1	1		1
Flue Gas, Wet		180										1		1											1	1	1		1
Fluoboric Acid	10.0%	100			1		1	1				1		1			1	1		1	1	1			1	1	1		1
Fluoboric Acid	10.0%	150																					2	2			2		2
Fluoboric Acid		100										1		1				1			1				1	1	1		1

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Fluoboric Acid		150										1		1											1	1	1		1
Fluosilicic Acid	10.0%	75			1				1			1	1	1			1	1			1	1	1	1	1	1	1	1	1
Fluosilicic Acid	20.0%	75			2				2			1	1	1			2				2				1	1	1	1	1
Fluosilicic Acid	35.0%	100										2	1	2											2	2	2	1	2
Fluosilicic Acid	Sat.	100										2	2	2											2	2	2	2	2
Formaldehyde	25.0%	75			1		2	2	1			1	1	1			1				1				1	1	1	1	1
Formaldehyde	37.0%	75			1		2	2	1		2	1	1	1			1	2		1	1	2	1	1	1	1	1	1	1
Formaldehyde	37.0%	100										2	1	1						1			2	1	2	1	2	1	1
Formaldehyde	37.0%	150										2	2	2									2	1	2	2	2	2	1
Formaldehyde	50.0%	100										1		1										1	1	1	1		1
Formaldehyde	50.0%	150										2	2	2										1			2	2	1
Formaldehyde 37%, Methanol 15%		75										1		1											1	1	1		1
Formamide	20.0%	75										2		1											2	1	2		1
Formamide		75										2	2	2											2	2	2	2	2
Formic Acid	2.0%	100										1	1	1									1	1	1	1	1	1	1
Formic Acid	10.0%	75			2		2	2	2	2	2	1	1	1			2	1	2	1	2	1	1	1	1	1	1	1	1
Formic Acid	25.0%	75			2			2	2			2	1	1			2	2		2	2	2	1	1	2	1	2	1	1
Formic Acid	25.0%	100																					2	2			2		2
Formic Acid	50.0%	75			4				4			2	2	1			4				4				2	1	2	2	1
Formic Acid	80.0%	75			4		4	4	4		2	2	2	2			4	4		4	4	4	2	2	2	2	2	2	2
Formic Acid	98.0%	75												2									2	2		2			2
Formic Acid 2%, Acetic Acid 2%		150																		2									
Fuel Oil		120										1		1				1				1			1	1	1		1
Fuel Oil #1		75		1	1	2	1	1	1		2	2	1	1		1	1	1		1	1	1			2	1	2	1	1
Furfural	5.0%	75										1	1	1											1	1	1	1	1
Furfural	10.0%	75										2		1				2				2			2	1	2		1
Furfural		75										3		2									3	2	3	2	3		2
Furfuryl Alcohol	20.0%	100										2		1										1	2	1	2		1
Furfuryl Alcohol		75					3	3			3	3	1	1				2		3		2	4	1	4	1	4	1	1
Gallic Acid	Sat.	75											2	1												1		2	1
Gasoline (Leaded)		75			1				1		2	1		1			1				1			1	1	1	1		1
Gasoline (Unleaded)		100		1	1	1	1	1	1	3	2	1		1		1	1	1	1	1	1	1		1	1	1	1		1

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Gasoline 30%, Cresylic Acid 21%, NaOH 13%		100										2		1											2	1	2		1
Gasoline 30%, Cresylic Acid 21%, NaOH 13%		150										2		2											2	2	2		2
Gasoline 90%, Ethanol 10% (Unleaded Gasoline)		100										3		1						2			3	1		1			1
Gasoline 90%, Methanol 10% (Unleaded Gasoline)		100										3		1									4	1		1			1
Glucose		75			1		1	1	1			1	1	1			1	1			1	1			1	1	1	1	1
Glutamic Acid	50.0%	100										1		1											1	1	1		1
Glutaraldehyde	50.0%	100										1		1											1	1	1		1
Glutaric Acid	50.0%	100										1		1											1	1	1		1
Glycerine (Glycerol)		100					1	1	1		1	1	1	1				1			1				1	1	1	1	1
Glycerine (Glycerol)		180										1	1	1											1	1	1	1	1
Glycol		100										1		1											1	1	1		1
Glycolic Acid	35.0%	100										2	1	1									2	1	2	1	2	1	1
Glycolic Acid	70.0%	75										2	2	2										1	2	2	2	2	2
Glycolic Acid		75										1		1				2			2				1	1	1		1
Glyconic Acid	50.0%	75										1		1											1	1	1		1
Glyoxal	40.0%	75										2		1											2	1	2		1
Glyoxylic Acid	50.0%	100										1		1									1	1	1	1	1		1
Glyoxylic Acid	50.0%	150										2		1									2	1			2		1
Grapefruit Juice		75										1													1		1		
Grapefruit Juice		150										1													1		1		
Heptane		75			1				1			1	1	1			1	1			1	1			1	1	1	1	1
Heptane		120										1		1				1				1			1	1	1		1
Heptane Sulfonic Acid		75										1		1									1	1	1	1	1		1
Heptanoic Acid (Heptoic Acid)	95.0%	100										1		1									1	1	1	1	1		1
Heptanoic Acid (Heptoic Acid)	95.0%	150										2		1									2	1	2	1	2		1
Heptanoic Acid (Heptoic Acid)		100										1		1									1	1	1	1	1		1

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Heptanoic Acid (Heptoic Acid)		150										2		1									2	1	2	1	2		1
Hexachlorocyclopentadiene		150												1										1		1			1
Hexachloroethane		75										2		1										1	2	1	2		1
Hexadecanol		100										1		1											1	1	1		1
Hexamethylenetetramine	40.0%	75										2		1											2	1	2		1
Hexane		75			1				1			1	1	1			1	1			1	1		1	1	1	1	1	1
Hexanoic Acid		75										2		1											2	1	2		1
Hexylene Glycol		75										1		1										1	1	1	1		1
Hexylene Glycol Ammonium Chloride	75.0%	75										1	1	1											1	1	1	1	1
Hydraulic Fluid		75		1	1	2	1	1	1		2	2		1		1	1	1	1	1	1	1			2	1	2		1
Hydrazine	10.0%	75											1	2												2		1	2
Hydrazine	35.0%	75										3	2	2				2			2					2		3	2
Hydrazine	70.0%	75											3	3												3		3	3
Hydrazine 5%, Sodium Phosphate 10%		75												2												2			2
Hydriodic Acid	40.0%	75										1		1											1	1	1		1
Hydriodic Acid	58.0%	75										2		1				1			1				2	1	2		1
Hydrobromic Acid	3.0%	150										2		1									2	1	2	1	2		1
Hydrobromic Acid	10.0%	150										2		1									2	1	2	1	2		1
Hydrobromic Acid	18.0%	100										1	1	1										1	1	1	1	1	1
Hydrobromic Acid	20.0%	150										1		1									1	1	1	1	1		1
Hydrobromic Acid	25.0%	100										1	1	1											1	1	1	1	1
Hydrobromic Acid	48.0%	100										1	1	1											1	1	1	1	1
Hydrobromic Acid	62.0%	100										2	2	2											2	2	2	2	2
Hydrobromic Acid 40%, Hydrochloric Acid 2%		100												2												2			2
Hydrochloric Acid	1.0%	75			1		2	2	1		2	1	1	1			1	1	1	1	1	1			1	1	1	1	1
Hydrochloric Acid	5.0%	75		1		1	1	1	1		2	1	1	1		1			1	1			1	1	1	1	1	1	1
Hydrochloric Acid	5.0%	150										2	1	1									2	1			2	1	1
Hydrochloric Acid	10.0%	75		1	1	1	1	1	1	2	2	1	1	1		1	1	1	1	1	1	1	1	1	1	1	1	1	1
Hydrochloric Acid	10.0%	150										2	1	1				2		3		2	2	1				1	1

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Hydrochloric Acid	20.0%	75			1		1	1	1		2	1	1	1			1	1		1	1	1	1	1	2	2	1	1	1
Hydrochloric Acid	20.0%	150			2				2			2	2	2			2	2			2	2	2	2			2	2	2
Hydrochloric Acid	30.0%	75		2	2	2	3	3	1			2	1	1		3	2	2	2	2	2	2	2	1			2	1	1
Hydrochloric Acid	30.0%	150			2							2	2	2			2			2	2		2	2			2	2	2
Hydrochloric Acid	37.0%	75		2	1	2	3	3	1		2	2	2	1		3	1		3	2	1		2	1	2	1	2	2	1
Hydrochloric Acid	37.0%	100										2	2	1						2				1			2	2	1
Hydrochloric Acid	37.0%	150										3	3	2					3					2			3	3	2
Hydrocyanic Acid	Sat.	100										1	1	1											1	1	1	1	1
Hydrofluoric Acid	0.5%	150										1*	2*	1*										1*	1*	1*	1*	2*	1*
Hydrofluoric Acid	3.0%	100																					2*	1*			2*		1*
Hydrofluoric Acid	10.0%	75			1*		3*	3*	1*			1*	2*	1*			1*		3*	2*	1*		2*	1*	1*	1*	1*	2*	1*
Hydrofluoric Acid	10.0%	150			2							2*		2*			2*			2*	2*		2*	2*	2*	2*	2*		2*
Hydrofluoric Acid	20.0%	75		3*		3*						2*		1*		3*							2*	1*			2*		1*
Hydrofluoric Acid	20.0%	150										3*		2*						2*			3*	2*	3*	2*	3*		2*
Hydrofluoric Acid	40.0%	75			2*		2*	2*	2*		2*	2*	2*	2*			2*			2*	2*			2*	2*	2*	2*	2*	2*
Hydrofluoric Acid	49.0%	75		3*		2*								2*		3								2*		2*			2*
Hydrofluoric Acid	55.0%	100												2*						2*				2*		2*			2*
Hydrofluoric Acid 15%, Nitric Acid 15%		75												1*												1*			1*
Hydrofluosilicic Acid	10.0%	100										1	1	1									1	1	1	1	1	1	1
Hydrofluosilicic Acid	20.0%	100									3	1	1	1						1			1	1	1	1	1	1	1
Hydrofluosilicic Acid	35.0%	100										2	1	2										2		2	2	1	2
Hydrogen Peroxide	3.0%	75			1		2	2	1		2	1	2	1			1		2	2	1		1	1	1	1	1	2	1
Hydrogen Peroxide	10.0%	75			2				2			1		1			2				2		1	1	1	1	1		1
Hydrogen Peroxide	30.0%	75		3	3	3	2	2	2	3	3	2	3	1		3	2			2	2		2	1	2	1	2	3	1
Hydrogen Peroxide	35.0%	75												1										1					1
Hydrogen Peroxide	50.0%	75			4				4			3	2	2			4				4			2	3	2	3	2	2
Hydrogen Peroxide	70.0%	75			4		3	3	4		3	3	2	2			4			4	3	4		2	3	2	3	2	2
Hydrogen Sulfide	Sat.	120										1		1				1				1			1	1	1		1
Hydroxyacetic Acid	35.0%	75										1	1	2											1	2	1	1	2
Hydroxyacetic Acid	70.0%	75										2	2	2											2	2	2	2	2
Hydroxylamine Sulfonate	30.0%	150										2		1									2	1			2		1
Hypochlorous Acid	10.0%	75										1	1	1											1	1	1	1	1
Hypochlorous Acid	20.0%	75										2	2												2		2	2	
Hypochlorous Acid		75										2	2												2		2	2	

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Hypophosphorous Acid	50.0%	75										1	1	1											1	1	1	1	1
Iminoethyl Alcohol		75											1															1	
Iodine		100										1		1			2					2	1	1	1	1	1		1
Isoamyl Alcohol	20.0%	100										1		1											1	1	1		1
Isoamyl Alcohol		75										1		1											1	1	1		1
Isobromyl Acetate		150										1		1											1	1	1		1
Isobutyl Acetate		100										3		1											3	1	3		1
Isobutyl Alcohol	20.0%	100										1		1											1	1	1		1
Isobutyl Alcohol		75										1		1											1	1	1		1
Isodecyl Alcohol		100										1		1											1	1	1		1
Isononyl Alcohol		100										1		1											1	1	1		1
Isooctyl Adipate		100										1		1											1	1	1		1
Isooctyl Alcohol		100										1		1											1	1	1		1
Isophorone		75										2		1			1					1		1	2	1	2		1
Isophorone		100												1										1		1			1
Isopropanol Amine		75										1		1											1	1	1		1
Isopropyl Acetate		75										3		2			1					1	3	2			3		2
Isopropyl Alcohol	10.0%	75										1	1	1											1	1	1	1	1
Isopropyl Alcohol		75		2		2			1			1	2	1		2		1			1	1	1	1	1	1	1	2	1
Isopropyl Alcohol		100										1		1			1				1	1	1	1	1	1	1		1
Isopropyl Alcohol		150										3	3	2						2			3	2	3	2	3	3	2
Isopropyl Amine	50.0%	75										1		1											1	1	1		1
Isopropyl Amine		75										3	3	2											3	2	3	3	2
Isopropyl Ether		100										3		1											3	1	3		1
Isopropyl Myristate		100										1		1											1	1	1		1
Isopropyl Palmitate		100										1		1											1	1	1		1
Itaconic Acid	10.0%	75										1	1	1											1	1	1	1	1
Itaconic Acid	25.0%	75										1	2	1											1	1	1	2	1
Jet Fuel		75		1	1	1	1	1	1		2	1		1		1	1	1		1	1	1	1	1	1	1	1		1
Kerosene		100			1				1	2		1	1	1			1	1		1	1	1	1	1	1	1	1	1	1
Kerosene		120										1		1			1				1	1	1	1	1	1	1		1
Kerosene		150			1				1			2	2	1			1	1		1	1	1	2	1	2	1	2	2	1
Lactic Acid	2.0%	150			1							1	1	1			1	1		1	1	1	1	1	1	1	1	1	1
Lactic Acid	8.5%	75		2	1	2	1	1	1	2	2	1	1	1		2	1	1	2	1	1	1	1	1	1	1	1	1	1
Lactic Acid	10.0%	75			1				1			1		1			1	1			1	1	1	1	1	1	1		1

* Double Veil Coat Recommended																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																															
--------------------------------	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

			* Double Veil Coat Recommended																										
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Liquor - Green (Sulfate Process - Thilmany)		130			2							1		1			2	1			2	1			1	1	1		1
Liquor - Green (Sulfate Process - Thilmany)		185			2							2		2			2				2				2	2	2		2
Liquor - Red (Weak)		190										2		2									2	2	2	2	2		2
Liquor - White		75			1		2	2	1		2	1		1			1				1		1	1	1	1	1		1
Liquor - White		140										1		1				1			1		1	1	1	1	1		1
Liquor - White		220															2		2		2								
Lithium Bromide	Sat.	100										2		1			2				2	2	1			2		1	
Lithium Carbonate		100										1		1										1	1	1		1	
Lithium Chloride	40.0%	100										1	1	1			1				1			1	1	1	1	1	
Lithium Chloride	40.0%	120										1		1			1				1			1	1	1		1	
Lithium Chloride	40.0%	150										1		1										1	1	1		1	
Lithium Chloride	Sat.	100										1		1										1	1	1		1	
Lithium Hydroxide	Sat.	100										1	2	1			1				1	1	1	1	1	1	1	2	1
Lithium Hydroxide	Sat.	150										1		2										1	2	1		2	
Lithium Hypochlorite		100										1		2			2				2	1	2	1	2	1		2	
Magnesium Bisulfite		100										1		1			1				1	1	1	1	1	1	1		1
Magnesium Bisulfite		150										1		1			1				1	2	1	2	1	2		1	
Magnesium Bisulfite		180										2		2									2	2	2	2	2		2
Magnesium Carbonate		100										1		1			1				1	1	1	1	1	1		1	
Magnesium Chloride	10.0%	75					2	2			2	1	1	1											1	1	1	1	1
Magnesium Chloride	Sat.	100										1	1	1			1				1			1	1	1	1	1	
Magnesium Chloride	Sat.	120										1		1			1				1			1	1	1		1	
Magnesium Fluosilicate		100										1		1											1	1	1		1
Magnesium Fluosilicate		150										2		1											2	1	2		1
Magnesium Hydroxide	10.0%	100										1		1			1				1	1	1	1	1	1	1		1
Magnesium Hydroxide	10.0%	150										2		1								2	1	2	1	2		1	
Magnesium Hydroxide	20.0%	100										1		1			1				1	1	1	1	1	1	1		1
Magnesium Hydroxide	Sat.	75			1		2	2	1		2	1		1		1	1			1	1	1	1	1	1	1	1		1
Magnesium Hydroxide	Sat.	100										1		1			1				1	1	1	1	1	1	1		1
Magnesium Nitrate	Sat.	100										1		1											1	1	1		1
Magnesium Sulfate	Sat.	100										1	1	1			1				1				1	1	1	1	1
Maleic Acid	5.0%	100										1	1	1											1	1	1	1	1
Maleic Acid	30.0%	75			1				1			2				1					1				2		2		

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Maleic Acid	50.0%	150										1	2	1						3			1	1	1	1	1	2	1
Maleic Acid	Sat.	100										1	1	1			1				1			1	1	1	1	1	1
Maleic Anhydride		150										2		1									2	1	2	1	2		1
Maleic Anhydride		200										2		2									2	2	2	2	2		2
Malic Acid	10.0%	100											2	1												1		2	1
Malic Acid		100										1		1			1				1			1	1	1			1
Mercaptoacetic Acid		75										3		1											3	1	3		1
Mercaptoethanol-2		100												1												1			1
Mercuric Chloride		120										1		1			1				1			1	1	1			1
Mercurous Chloride		120										1		1			1				1			1	1	1			1
Methacrylic Acid	5.0%	100										1	1	1									1	1	1	1	1	1	1
Methacrylic Acid	5.0%	150										2	3										2		2		2	3	
Methacrylic Acid	25.0%	100										2		1										2	1	2			1
Methacrylic Acid	50.0%	150			2								3	3			2			3	2		3	2		3		3	3
Methacrylic Acid	Glacial	75										2	1	1									2	1	2	1	2	1	1
Methacrylic Acid	Glacial	120										3		2											3	1	3		1
Methane		75			1				1			2					1				1				2		2		
Methanesulfonic Acid	70.0%	100								2		1		1									1	1	1	1	1		1
Methene bis 4-cyclohexylamine		100										1		1									1	1	1	1	1		1
Methoxy (1) -2-Propanol		75										3		1											3	1	3		1
Methyl Acetate	20.0%	75										1		1									1	1	1	1	1		1
Methyl Acetate		75										3		2									3	2			3		2
Methyl Alcohol	5.0%	75										1		1									2	2	1	1	1		1
Methyl Alcohol	20.0%	75										2		1									2	2	2	1	2		1
Methyl Alcohol	30.0%	75			3				3			2	2	1			3				3		2	2	2	1	2	2	1
Methyl Alcohol	90.0%	75										3	2	2									2	2	3	2	3	2	2
Methyl Alcohol		75		3	3	3	3	3	3	3	3	3	2	2		3	3	2	3	2	3	2	2	2	3	2	3	2	2
Methyl Amine		75										3		2											3	2	3		2
Methyl Amyl Alcohol		75										2		1			1				1		2	1	2	1	2		1
Methyl bis amino-propylamine		100										2		2									2	2	2	2	2		2
Methyl Bromide	10.0%	75										2		2											2	2	2		2
Methyl Bromide		75										3		2											3	2	3		2
Methyl Chloroform		75											2															2	

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Methyl Chloroformate		75										3		2									3	2	3	2	3		2
Methyl Diethanolamine	50.0%	75										1		1									1	1	1	1	1		1
Methyl Ethyl Ketone (MEK)	20.0%	75										1		1									1	1	1	1	1		1
Methyl Ethyl Ketone (MEK)		75			3		3	3	3		4	3	3	2		3	2	3	3	3	2	3	2	3	2	3	3	3	2
Methyl Ethyl Ketone Peroxide (MEKP)		75												2									2		2				2
Methyl Formate	5.0%	75										2		1											2	1	2		1
Methyl Hydrazine		75										3		2											3	2	3		2
Methyl Iso Butyl Ketone (MIBK)		75			2				2			3		1		2	1			2	1	3	1	3	1	3		1	
Methyl Mercaptan		75										2		1											2	1	2		1
Methyl Methacrylate		75										3		2			2				2	3	2	3	2	3		2	
Methyl Oleate		75										1		1			1				1	1	1	1	1	1		1	
Methyl Styrene		75										2		1											2	1	2		1
Methyl Tert-Butyl Ether (MTBE)		100										3		2								3	2	3	2	3		2	
Methyl(2)-3-Butenenitrile		75										3		2											3	2	3		2
Methyl-(n), 2-Pyrrolidone (M-Pyrol)	10.0%	75										3		2											3	2	3		2
Methyl-(n), 2-Pyrrolidone (M-Pyrol)		75		4	4	4	4	4	4		3	4		2		4	4		4	3	4				4	2	4		2
Methylamine	20.0%	75										2		2											2	2	2		2
Methylamine	40.0%	75										2		2											2	2	2		2
Methylamine		75			2				2			3		2		2				2					3	2	3		2
Methyldiethanolamine	20.0%	100										1		1									1	1	1	1	1		1
Methyldiethanolamine	50.0%	100										1		1									1	1	1	1	1		1
Methyldiethanolamine		100										1		1									1	1	1	1	1		1
Methyldiethanolamine		120										2		1					2				2	1	2	1	2		1
Methylene Chloride		75			3		4	4	3	4	4	4	4	3		3		4	4	3		4	3	4	3	4	4	4	3
Methylstyrene		100										2		1											2	1	2		1
Mineral Oil		120										1	1	1			1				1	1	1	1	1	1	1	1	1
Mineral Spirits		75			1			1	1			1		1		1	1		1	1	1	1	1	1	1	1	1		1
Mineral Spirits		120										1		1			1		1		1	1	1	1	1	1	1		1

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Molasses		100										1		1			1					1	1		1	1	1		1
Molasses		150										1										1		1		1			
Monochlorobenzene		75										2		1										2	1	2		1	
Morpholine	10.0%	75										2	1	2										2	2	2	1	2	
Morpholine	20.0%	75										2		2										2	2	2		2	
Morpholine		75										3		2										3	2	3		2	
Mustard - Yellow		75										1										1		1		1			
Myristic Acid		100										1		1										1	1	1		1	
Naptha		75			1				1			1	1	1			1	1			1	1		1	1	1	1	1	
Naptha		100										1		1			1				1			1	1	1		1	
Naptha Sulfonic Acid (Sour Oil)		100												1											1			1	
Napthalene		100										1	2	1			1				1			1	1	1	2	1	
Napthalene		120												1			1				1				1			1	
Napthenic Acid		100										2		1			1				1	2	1			2		1	
Neopentyl Glycidyl Ether	90.0%	100											1														1		
Nickel Chloride	Sat.	100										1	1	1										1	1	1	1	1	
Nickel Nitrate	Sat.	100										1	1	1										1	1	1	1	1	
Nickel Sulfamate		100										1		1										1	1	1		1	
Nickel Sulfate	Sat.	100										1	1	1										1	1	1	1	1	
Nitric Acid	1.0%	75			1		1	1	1		2	1	1	1			1		1		1		1	1	1	1	1	1	
Nitric Acid	5.0%	75		2	1	2	1	1	1			1	1	1		2	1	1	2	1	1	1	1	1	1	1	1	1	
Nitric Acid	5.0%	150										2	1	1				2	3		2	2	1	2	1	2	1	1	
Nitric Acid	10.0%	75		2	2	2	2	2	1		2	1	1	1		2	2	2	2	2	1	2		1	1	1	1	1	
Nitric Acid	10.0%	150										2	1	2					3			2	2	2	2	2	1	2	
Nitric Acid	20.0%	75			2		3	2	2	2		1	1	1			2			2		1	1	1	1	1	1	1	
Nitric Acid	30.0%	75			2							2	1	1			2	2		2	2	2	1	2	1	2	1	1	
Nitric Acid	35.0%	75																				2	2						
Nitric Acid	40.0%	75			3		4	4	3			3	1	2			3				3		2	2	3	2	3	1	2
Nitric Acid	50.0%	75		4	4	4	4	4	4		4	4	2	3		4	4		4		4		3	3	4	3	4	2	3
Nitric Acid	70.0%	75			4		4	4	4		4	4	3	4			4			4	4		4	4	4	4	4	3	4
Nitric Acid 10%, Chromic Acid 5%,		100										2		1										2	1	2		1	
Nitric Acid 15%, Hydrofluoric Acid 15%		75										2*		1*										2*	1*	2*		1*	

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Nitric Acid 20%, Hydrofluoric Acid 6%		100										1*		1*											1*	1*	1*		1*
Nitric Acid 20%, Sulfuric Acid 20%		75										2		1											2	1	2		1
Nitric Acid 20%, Sulfuric Acid 5%, Phosphoric Acid 2%		75												1												1			1
Nitric Acid 24%, Phosphoric Acid 23%		75										2		1											2	1	2		1
Nitric Acid 25%, Hydrofluoric Acid 3%		75										2*		1*											2*	1*	2*		1*
Nitric Acid 35%, Hydrofluoric Acid 5%		75										3*		2*											3*	2*	3*		2*
Nitric Acid 35%, Hydrofluoric Acid 5%		75										3*		2*											3*	2*	3*		2*
Nitric Acid 37%, Sulfuric Acid 6%, Phosphoric Acid 2%		75		3	2	3			2			2		2		3	2	2			2	2	2	2	2	2	2		2
Nitric Acid 5%, Acetic Acid 3%, Chromic Oxide 3%		100										1		1											1	1	1		1
Nitric Acid 5%, Phosphoric Acid 5%		75										1		1											1	1	1		1
Nitrobenzene		75										3		1				1			1	3	1	3	3	1	3		1
Nitrophenol		75										3		1											3	1	3		1
Nitropropane-(2)		100										3		1									3	1	3	1	3		1
Nonyl Phenol		75										1	1										1	1	1	1	1	1	1
Nonyl Phenol		120										1		1									2	1	1	1	1		1
Nonyl Phenol		150										2		1									2	1	2	1	2		1
Octanoic Acid	Sat.	100										1	1	1									1	1	1	1	1	1	1
Octanoic Acid	Sat.	150										1		1									1	1	1	1	1		1
Octyl Alcohol		100										1		1				1			1		1	1	1	1	1		1
Octyl-(n) Mercaptan		100										1		1									1	1	1	1	1		1
Octyl-(n) Mercaptan		150										1		1									1	1	1	1	1		1
Oil - Crude		150			1							1		1			1			1	1		1	1	1	1	1		1

* Double Veil Coat Recommended																														
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662	
Oil - Crude		200										1		1									1	1	1	1	1	1		1
Oil - Crude (Sour)		100										1		1			1					1	1	1	1	1	1		1	
Oil - Crude (Sour)		120										1		1			1					1	1	1	1	1	1		1	
Oil - Crude (Sweet)		100										1		1			1					1	1	1	1	1	1		1	
Oil - Crude (Sweet)		120										1		1			1					1	1	1	1	1	1		1	
Oil - Jet Turbine		75			2		2	2	2		2					2		2	2	2	2									
Oil - Mineral		120										1		1			1					1	1	1	1	1	1		1	
Oil - Motor		120										1		1			1					1	1	1	1	1	1		1	
Oil - Vegetable		120										1		1			1					1	1	1	1	1	1		1	
Oleic Acid	10.0%	75			1				1			1	1	1			1		2		1		1	1	1	1	1	1	1	
Oleic Acid		75			2		3	3	2	3	2	1	1	1			2	1	3	1	2	1	1	1	1	1	1	1	1	
Oleic Acid		100										1		1			1					1	1	1	1	1	1		1	
Oleic Acid		120										1		1			2				2	1	1	1	1	1	1		1	
Oleum (Fuming Sulfuric)		75			2				2			3		2			2	2			2	2	3	2			3		2	
Ortho Dichlorobenzene		100										3		1											3	1	3		1	
Oxalic Acid	5.0%	75								3		1	1	1									1	1	1	1	1	1	1	
Oxalic Acid	10.0%	100			2							1	1	1			2	2		2	2	2	1	1	1	1	1	1	1	
Oxalic Acid	10.0%	150			2							2	1	1			2	2		2	2	2	2	1	2	1	2	1	1	
Oxalic Acid		75										1		1			2				2	1	1	1	1	1		1		
Ozone	3.0%	75										2		2												2		2	2	
Ozone	2mg/L	75										1		1											1	1	1		1	
Ozone	0.5ppm	75			2				2			2		1		2				2				2	1	2		1		
Palmitic Acid		75			2				2			1		1		2				2		1	1	1	1	1		1		
Palmitic Acid		150										1		1									1	1	1	1	1		1	
Pentabromo Diphenyl Oxide		100										2		1											2	1	2		1	
Pentachloroethane		100										3		2			2				2				3	2	3		2	
Pentachlorophenol		75										1		1											1	1	1		1	
Pentane		75			1				1			2				1				1					2		2			
Pentanoic Acid		100										2		1									2	1	2	1	2		1	
Pentanoic Acid		150										2		1									2	1	2	1	2		1	
Peracetic Acid	20.0%	75										1		1											1	1	1		1	
Peracetic Acid	35.0%	75										3		2											3	2	3		2	
Perchloric Acid	10.0%	75										1	2	1									1	1	1	1	1	2	1	
Perchloric Acid	30.0%	75										2	2	1									2	1	2	1	2	2	1	

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Perchloroethylene		75										2	2	1				1				1	2	1	2	1	2	2	1
Phenol (Carbolic Acid)	5.0%	75		3		3	2	2	2		2	3	1	1		3			3	2			3	1			3	1	1
Phenol (Carbolic Acid)	5.0%	150										3	3	2					3				3	2	3	2	3	3	2
Phenol (Carbolic Acid)	10.0%	75										2	2	2					2				2	2	2	2	2	2	2
Phenol (Carbolic Acid)	15.0%	75										3	3	2					3				3	2			3	3	2
Phenol (Carbolic Acid)	50.0%	75			3		4	4	3		4	3	4	2			3	3		4	3	3	3	2			3	4	2
Phenol (Carbolic Acid)	88.0%	75			3		4	4	3		4	4	4	3			3	3		4	3	3	3	2			3	4	2
Phenol Formaldehyde Resin		75										2		1											2	1	2		1
Phenol Sulfonic Acid		75										3		2											3	2	3		2
Phosphoric 80%, Nitric 4%		100											1															1	
Phosphoric Acid	1.0%	75			1		1	1	1			1	1	1			1	1	1	1	1	1	1	1	1	1	1	1	1
Phosphoric Acid	5.0%	75			1		1	1	1			1	1	1			1	1	1	1	1	1	1	1	1	1	1	1	1
Phosphoric Acid	5.0%	150										1	1	1						1					1	1	1	1	1
Phosphoric Acid	8.5%	75					1	1	1		2	1	1	1											1	1	1	1	1
Phosphoric Acid	10.0%	75		2	1	2	1	1	1		2	1	1	1		2	1	1	1	1	1	1	1	1	1	1	1	1	1
Phosphoric Acid	10.0%	120					1	1				1		1				1	1	1		1	1	1	1	1	1		1
Phosphoric Acid	10.0%	150										1		1				2				2	1	1	1	1	1		1
Phosphoric Acid	20.0%	75										1		1				1				1	1	1	1	1	1		1
Phosphoric Acid	20.0%	150			2							1	2	1			2	2		2	2	2	1	1	1	1	1	2	1
Phosphoric Acid	30.0%	75		3	1	3	2	2	1	2	2	1	1	1		3	1				1		1	1	1	1	1	1	1
Phosphoric Acid	40.0%	75			1		2	2	1			1		1			1	1	1	1	1	1	1	1	1	1	1		1
Phosphoric Acid	50.0%	75		2	1	2	2	2	1		2	1	1	1		2	1	1	2	1	1	1	1	1	1	1	1	1	1
Phosphoric Acid	54.0%	150										1	2	1						2			1	1	1	1	1	2	1
Phosphoric Acid	76.0%	150										2	2	1						2			2	1			2	2	1
Phosphoric Acid	86.0%	75		3	2	3	2	2	2		2	1	1	1		3	2		3	2	2		1	1	1	1	1	1	1
Phosphoric Acid	86.0%	150			3							2	2	2			3			3	3		2	2			2	2	2
Phosphoric Acid 45%, Sulfuric Acid 40%		75										1		1											1	1	1		1
Phosphoric Acid 85%, Sulfuric Acid 15%		75										2		1											2	1	2		1
Phosphoric Acid-Super		100										1	1	1									1	1			1	1	1
Phosphorus 70%, Hydrochloric 2%		100										1	1	1											1	1	1	1	1

			* Double Veil Coat Recommended																										
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Phosphorus Acid	70.0%	75			2		2	2	2			1		1		2			3	2		1	1	1	1		1		
Phosphorus Oxychloride		75										3	2	2			2				2	3	2	3	2	3	2	2	
Phosphorus Sesquisulfide		75											1														1		
Phosphorus Trichloride		100										3		2			2				2			3	2	3		2	
Phthalic Acid		75										1		1			2				2			1	1	1		1	
Phthalic Anhydride	Sat.	100										1	2	1										1	1	1	2	1	
Picric Acid	10.0%	75										3		1										3	1	3		1	
Picric Acid 1% in Ethanol		75										2		2			2				2	2	2	2	2	2		2	
Polyacrylamide		75										1		1										1	1	1		1	
Polyacrylic Acid		100										1		1										1	1	1		1	
Polyethyleneimine		100										1		1										1	1	1		1	
Polyphosphoric Acid		75										1		1										1	1	1		1	
Polytetrahydrofuran		150												2											2			2	
Polyvinyl Alcohol	10.0%	100										1	1	1										1	1	1	1	1	
Polyvinyl Alcohol		100										1	2	1										1	1	1	2	1	
Potassium Acetate		100										1		1			1				1	1	1	1	1	1		1	
Potassium Aluminum Sulfate	Sat.	100										1	1	1										1	1	1	1	1	
Potassium Bicarbonate	10.0%	100										1	2	1										1	1	1	2	1	
Potassium Bicarbonate		100										1		1										1	1	1		1	
Potassium Bromide	10.0%	75										1		1			1				1	1	1	1	1	1		1	
Potassium Bromide	30.0%	75			1				1			1		1			1				1		1	1	1	1		1	
Potassium Bromide	Sat.	75										1		1			1				1	1	1	1	1	1		1	
Potassium Carbonate	10.0%	75										1	2	1									1	1	1	1	1	2	1
Potassium Carbonate	25.0%	75										1	2	1									1	1	1	1	1	2	1
Potassium Carbonate	50.0%	75			1		1	1	1		2	1	2	1			1		1	1	1			1	1	1	2	1	
Potassium Chlorate		100										1		1			1				1	1	1	1	1	1		1	
Potassium Chloride	30.0%	75			1				1			1	1	1			1				1			1	1	1	1	1	
Potassium Chloride	45.0%	150										2	2	2						1			2	2			2	2	2
Potassium Chloride	50.0%	75			1		1	1	1		1	1	1	1			1			1	1			1	1	1	1	1	
Potassium Chloride	50.0%	150										2		2									2	2			2		2
Potassium Chloride	Sat.	75										1		1			1				1			1	1	1		1	
Potassium Chloride	Sat.	120										1		1			1				1			1	1	1		1	
Potassium Cyanide		100										1		1			1				1	1	1	1	1	1		1	

			* Double Veil Coat Recommended																										
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Potassium Dichromate	10.0%	75			1				1	2		1	1	1		1					1				1	1	1	1	1
Potassium Ferricyanide	Sat.	100										1		1											1	1	1		1
Potassium Ferrocyanide	25.0%	100										1		1									1	1			1		1
Potassium Ferrocyanide	25.0%	100										1		2									1	2			1		2
Potassium Ferrocyanide	Sat.	100										1	1	1											1	1	1	1	1
Potassium Fluoride	15.0%	100										1		1										1	1	1	1	1	1
Potassium Hydroxide	1.0%	75		1	1	1	1	1				1	1	1		1	1	1		1	1	1	1	1	1	1	1	1	1
Potassium Hydroxide	5.0%	150										1		2				1		1		1	1	2			1		2
Potassium Hydroxide	10.0%	150							1			2		2				1		1		1	2	2			2		2
Potassium Hydroxide	20.0%	75			1		1	1	1	3	2	1		1			1	1	1	1	1	1			1	1	1		1
Potassium Hydroxide	20.0%	150										2		2				1		1		1	2	2			2		2
Potassium Hydroxide	25.0%	75			1		1	1	1	3	2	1		1			1	1	1	1	1	1	1	1	1	1	1	1	1
Potassium Hydroxide	25.0%	150										2		2				1		1		1	2	2			2		2
Potassium Hydroxide	30.0%	75			1		1	1	1	3	2	1		2			1	1	1	1	1	1	1	2			1		2
Potassium Hydroxide	30.0%	150										2		2				1		1		1	2	2			2		2
Potassium Hydroxide	45.0%	150										2		2						1			2	2			2		2
Potassium Hydroxide	50.0%	75			1		1	1	1		2	1		1			1	1		1	1	1	1	1			1		1
Potassium Hydroxide	50.0%	150										2		2				1		1		1	2	2			2		2
Potassium Hydroxide	65.0%	100			1							1					1	1		1	1	1			1		1		
Potassium Hydroxide 44%, Acrylic Acid 21%		100										1		1						1			1	1			1		1
Potassium Iodine		100										1		1											1	1	1		1
Potassium Nitrate		100										1	1	1				1				1	1	1	1	1	1	1	1
Potassium Nitrate		120										1	1	1				1				1	1	1	1	1	1	1	1
Potassium Oxalate		100										1		1											1	1	1		1
Potassium Permanganate	5.0%	150										2	2	1									1	1	2	1	2	2	1
Potassium Permanganate		100			1				1			2	2	1			1	2			1		1	1	2	1	2	2	1
Potassium Persulfate		100										1	2	1				1				1	1	1	1	1	1	2	1
Potassium Phosphate	10.0%	75					1	1			1	1		1						1					1	1	1		1
Potassium Pyrophosphate	60.0%	75										1		1											1	1	1		1

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Potassium Pyrophosphate		100										2	1	1											2	1	2	1	1
Potassium Silicofluoride		100										2*		2*											2*	2*	2*		2*
Potassium Sulfate		100										1	1	1				1				1	1	1	1	1	1	1	1
Potassium Sulfite	45.0%	100										1		1									1	1	1	1	1		1
Potassium Thiosulfate		100										1											1		1		1		
Potassium Dichromate		100										1		1				1				1		1	1	1		1	
Propionaldehyde		75										2		1										1	2	1	2		1
Propionic Acid	1.0%	100										1	1	1									1	1	1	1	1	1	1
Propionic Acid	5.0%	100										1		1									1	1	1	1	1		1
Propionic Acid	20.0%	100										1		1									1	1	1	1	1		1
Propionic Acid	50.0%	100										1		1				1				1	1	1	1	1	1		1
Propionic Acid	50.0%	120										1		1									1	1		1			1
Propionic Acid		75					4	4			4	3		2				2				2	3	2			3		2
Propionyl Chloride		100										3		2											3	2	3		2
Propyl Acetate - N		75										3		2											3	2	3		2
Propyl Acetate - N		100										3		2											3	2	3		2
Propyl Alcohol - N		75										1		1											1	1	1		1
Propyl Aldehyde - N		75												2												2			2
Propyl Bromide		75										3		2											3	2	3		2
Propyl Chloride		75										3		2											3	2	3		2
Propylene Carbonate - Crude		100										1		1									1	1	1	1	1		1
Propylene Dichloride		100										3		1									3	1	3	1	3		1
Propylene Glycol		100										1	1	1									1	1	1	1	1	1	1
Propylene Glycol		120										1		1											1	1	1		1
Propylene Glycol Methyl Ether (PM)		75		2	2	2	3	3	2		3	3		1		3	2		3	3	2		3	1	3	1	3		1
Propylene Glycol Methyl Ether Acetate (PM Acetate)	20.0%	100										2		1									2	1			2		1
Propylene Glycol Methyl Ether Acetate (PM Acetate)		100										3		2									3	2			3		2
Propylene Oxide		75			2				2			4		3			2				2				4	3	4		3

			* Double Veil Coat Recommended																										
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Pyridine	20.0%	75										2		1				1				1			2	1	2		1
Pyridine		75										4	4	3			2					2	4	3	4	3	4	4	3
Quinoline	20.0%	75										2		1											2	1	2		1
Quinoline		75										4		2											4	2	4		2
Salicylic Acid	15.0%	100										1		1			1					1	1	1	1	1	1		1
Salicylic Acid	Sat.	100										1		1			1					1	1	1	1	1	1		1
Selenious Acid		100										1		1											1	1	1		1
Silver Nitrate		100										1	1	1			1					1	1	1	1	1	1	1	1
Silver Nitrate		120										1		1			1					1	1	1	1	1	1		1
Skydrol		75			1				1			2		1			1	1			1	1	2	1	2	1	2		1
Skydrol		100										2		1			1					1	2	1	2	1	2		1
Skydrol		120										2		1			1					1	2	1	2	1	2		1
Sodium Acetate		75			1				1			1	1	1			1	1			1	1	1	1	1	1	1	1	1
Sodium Acetate		120										1		1			1					1		1	1	1	1		1
Sodium Alkyl Benzene Sulfonate		75											1															1	
Sodium Aluminate	Sat.	75			1				1			1		1			1				1		1	1			1		1
Sodium Aluminate	Sat.	150										2		2									2	2			2		2
Sodium Ammonium Phosphate		100											1															1	
Sodium Benzoate	Sat.	100										1	1	1											1	1	1	1	1
Sodium Bicarbonate	Sat.	100										1	1	1			1					1	1	1	1	1	1	1	1
Sodium Bicarbonate	Sat.	120										1		1			1					1	1	1	1	1	1		1
Sodium Bifluoride		100										1*		1*									1*	1*	1*	1*	1*		1*
Sodium Bisulfate		75			1				1			1	1	1			1	1			1	1	1	1	1	1	1	1	1
Sodium Bisulfate		100										1		1			1					1	1	1	1	1	1		1
Sodium Bisulfate		120															1					1							
Sodium Bisulfide	35.0%	100			1							1	1	1			1	1		1	1	1			1	1	1	1	1
Sodium Bisulfide	65.0%	100										1	1	1											1	1	1	1	1
Sodium Bisulfite	10.0%	150										1		1									1	1	1	1	1		1
Sodium Bisulfite	20.0%	100										1		1			1					1	1	1	1	1	1		1
Sodium Bisulfite	20.0%	150										1		1									1	1	1	1	1		1
Sodium Bisulfite	35.0%	100										1	1	1									1	1	1	1	1	1	1
Sodium Bisulfite	35.0%	150										2		2									2	2			2		2
Sodium Bisulfite	40.0%	150										2	2	2									2	2			2	2	2

* Double Veil Coat Recommended																															
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662		
Sodium Bisulfite	50.0%	75					1	1			2	1	1	1									1	1	1	1	1	1	1	1	
Sodium Bisulfite	Sat.	75			1				1			1	1	1			1	1			1	1	1	1	1	1	1	1	1	1	
Sodium Bisulfite	Sat.	100										1		1				1				1	1	1	1	1	1			1	
Sodium Bisulfite	Sat.	150										2		2				1				1	2	2			2		2		
Sodium Borate	10.0%	120									1			1				1				1	1	1	1	1	1			1	
Sodium Borate	Sat.	75			1				1			1	1	1			1				1		1	1	1	1	1	1	1	1	
Sodium Bromate		100									1			1				1				1			1	1	1			1	
Sodium Bromide		75			1				1			1	1	1			1				1				1	1	1	1	1	1	
Sodium Carbonate	5.0%	75			1		1	1			2	1	1	1			1			1	1				1	1	1	1	1	1	
Sodium Carbonate	25.0%	100										1	2	1											1	1	1	2		1	
Sodium Carbonate	50.0%	100			2				1		2	1	2	1			2				2				1	1	1	2		1	
Sodium Carbonate		100			1				1			1	2	1			1	1			1	1	1	1	1	1	1	2		1	
Sodium Chlorate	5.0%	75			1		1	1			1	1	1	1			1	1		1	1	1	1	1	1	1	1	1	1	1	
Sodium Chlorate	25.0%	75			1		1	1			2	1	1	1			1	1		1	1	1	1	1	1	1	1	1	1	1	
Sodium Chlorate	48.0%	180										2	2	2						2		2	2	2	2	2	2	2	2	2	
Sodium Chlorate	50.0%	75			2		2	2			2	1	1	1			2		2	1			1	1	1	1	1	1	1	1	
Sodium Chlorate	Sat.	100										1	1	1				1				1	1	1	1	1	1	1	1	1	
Sodium Chloride	25.0%	150										1	1	1									2	1	1	1	1	1	1	1	
Sodium Chloride	30.0%	75		1		1				2		1		1									1	1	1	1	1			1	
Sodium Chloride	50.0%	75		1	1	1			1		2	1	1	1		1	1	1	1		1		1	1	1	1	1	1	1	1	
Sodium Chloride	Sat.	120										1	1	1				1		1		1	1	1	1	1	1	1	1	1	
Sodium Chloride	Sat.	150										1	1	1				1		1		1	1	1	1	1	1	1	1	1	
Sodium Chloride	Sat.	200										2	2	2						1					2	2	2	2	2	2	
Sodium Chloride 20%, Sodium Hydroxide 9%, Sodium Hypochlorite 5ppm		150										2											2		2		2				
Sodium Chloride 20%, Sodium Hydroxide 9%, Sodium Hypochlorite 5ppm		180										3											3		3		3				
Sodium Chlorite	2.0%	100										1	1	1										1	1	1	1	1	1	1	
Sodium Chlorite	25.0%	100										1	1	1										1	1	1	1	1	1	1	
Sodium Chlorite	Sat.	100										1	1	1				1				1		1	1	1	1	1	1	1	

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Sodium Chromate	50.0%	150										1		1										1	1	1	1		1
Sodium Chromate	Sat.	75			1				1			1	1	1			1	1			1	1	1	1	1	1	1	1	1
Sodium Citrate	40.0%	100										1											1		1		1		
Sodium Cyanide		120										1						1				1	1	1		1			1
Sodium Dichromate	10.0%	100										1	1	1				1				1	1	1	1	1	1	1	1
Sodium Dichromate	Sat.	100										1	1	1				1				1	1	1	1	1	1	1	1
Sodium Diphosphate		100										1		1											1	1	1		1
Sodium Dodecylbenzene Sulfonate	40.0%	75										1	1	1											1	1	1	1	1
Sodium Dodecylbenzene Sulfonate	Sat.	75										1		1											1	1	1		1
Sodium Ferricyanide	Sat.	100										1	1	1											1	1	1	1	1
Sodium Ferrocyanide	Sat.	100										1	1	1											1	1	1	1	1
Sodium Fluoride	Sat.	100										1*		1*				1*				1*	1*	1*	1*	1*	1*		1*
Sodium Fluorosilicate		75										1*		1*											1*	1*	1*		1*
Sodium Formate	10.0%	100										1		1									1	1	1	1	1		1
Sodium Formate	60.0%	120										1		1									1	1	1	1	1		1
Sodium Formate	60.0%	200										1		1									1	1	1	1	1		1
Sodium Hexametaphosphate	Sat.	75										1	1	2											1	2	1	1	2
Sodium Hydrogen Phosphate		100											1															1	
Sodium Hydrosulfide	5.0%	75					2	2			2	1	1	1									1	1	1	1	1	1	1
Sodium Hydrosulfide	25.0%	75									2	1	1	1									1	1	1	1	1	1	1
Sodium Hydrosulfide	40.0%	150										1		2									1	2	1	2	1		2
Sodium Hydrosulfide	65.0%	100											1	1										1		1		1	1
Sodium Hydrosulfide		100										1		1				2				2	1		1	1	1		1
Sodium Hydrosulfide		150										1		2									1	2			1		2
Sodium Hydrosulfite	10.0%	100										1		1									1	1	1	1	1		1
Sodium Hydrosulfite	10.0%	150										2		1									2	1	2	1	2		1
Sodium Hydrosulfite	25.0%	100										2		1									2	1	2	1	2		1

* Double Veil Coat Recommended																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																													
--------------------------------	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Sodium Hypophosphite	Sat	75										1		1				1				1			1	1	1		1
Sodium Hypophosphite	Sat.	120															1				1								
Sodium Lauryl Sulfate	20.0%	75										1		1			1				1	1	1	1	1	1	1		1
Sodium Lauryl Sulfate	20.0%	120										1		1			1				1	1	1	1	1	1	1		1
Sodium Lauryl Sulfate		75										1	2	1			1				1			1	1	1	2	1	
Sodium Metabisulfite		100										1		1										1	1	1		1	
Sodium Metabisulfite 45%, Chromic Acid 15%		100										2		1										2	1	2		1	
Sodium Methyldithiocarbamate		100										1		1										1	1	1		1	
Sodium Monophosphate	Sat.	75										1		1										1	1	1		1	
Sodium Nitrate	Sat.	100										1	1	1										1	1	1	1	1	
Sodium Nitrite	Sat.	100										1	1											1		1	1		
Sodium Oxalate		75										1		1			1				1	1	1	1	1	1		1	
Sodium Oxalate		120										1		1			1				1		1		1			1	
Sodium Perchlorate	60.0%	75										2		2										2	2	2		2	
Sodium Peroxide		100										1		1			1				1	1	1	1	1	1		1	
Sodium Persulfate	20.0%	75										1		1										1	1	1		1	
Sodium Persulfate	Sat.	75										1		1										1	1	1		1	
Sodium Phosphate		75										1		1			1				1	1	1	1	1	1		1	
Sodium Phosphate		120										1		1			1				1		1	1	1	1		1	
Sodium Phosphate Acid		75			1				1			1				1				1				1		1			
Sodium Polyacrylate		100										1		1										1	1	1		1	
Sodium Sarcosinate	40.0%	100										1		1										1	1	1		1	
Sodium Silicate	6.0%	100										1	1	1										1	1	1	1	1	
Sodium Sulfate	15.0%	75										1		1			1				1	1	1	1	1	1		1	
Sodium Sulfate	15.0%	120										1		1			1				1	1	1	1	1	1		1	
Sodium Sulfate	Sat.	75			2				2		2	1	1	1			2				2		1	1	1	1	1	1	
Sodium Sulfate	Sat.	120										1		1			1				1		1	1	1	1		1	
Sodium Sulphydrate	15.0%	100										1	1											1		1	1		
Sodium Sulphydrate	45.0%	100										1	1											1		1	1		
Sodium Sulphydrate	65.0%	100											1														1		
Sodium Sulfide	10.0%	100										1	2	1										1	1	1	2	1	
Sodium Sulfide	Sat.	100										1	2	1			1				1		1	1	1	1	2	1	
Sodium Sulfide	Sat.	120												1			1				1		1		1			1	

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Sodium Sulfite	25.0%	100										1		1									1	1	1	1	1		1
Sodium Sulfite	50.0%	100										1		1									1	1	1	1	1		1
Sodium Sulfite	50.0%	150										1		1									1	1		1	1		1
Sodium Sulfite	Sat.	100										1	1	1				1				1		1	1	1	1	1	1
Sodium Sulfite	Sat.	120												1				1				1		1		1			1
Sodium Tartrate		75										1		1				1				1	1	1	1	1	1		1
Sodium Tartrate		120										1		1				1				1		1	1	1	1		1
Sodium Tetraborate	Sat.	100										1	1	1											1	1	1	1	1
Sodium Tetrachlorophenate	13.0%	100											2															2	
Sodium Thiocyanate		100										1		1											1	1	1		1
Sodium Thiosulfate		120										1		1				1				1			1	1	1		1
Sodium Toluene Sulfonate		120										1											1		1		1		
Sodium Triphosphate	Sat.	75										1	2	1				1				1	1	1	1	1	1	2	1
Sodium Triphosphate	Sat.	120										1		1				1				1			1	1	1		1
Sodium Vinyl Sulfonate		100										1		1									1	1	1	1	1		1
Sodium Xylene Sulfonate	40.0%	100										1	1	1											1	1	1	1	1
Sodium Xylene Sulfonate		100										1		1											1	1	1		1
Soy Sauce		100										1											1		1		1		
Soy Sauce		150										1											1		1		1		
Soybean Oil		75										1		1				1				1	1		1	1	1		1
Soybean Oil		120												1				1				1	1			1			1
Stannic Chloride		75										1		1				1				1			1	1	1		1
Stannic Chloride		120												1				1				1	1	1		1			1
Stannous Chloride	10.0%	150										1	1	1						1			1	1	1	1	1	1	1
Stannous Chloride	55.0%	100										1	1	1						1			1	1	1	1	1	1	1
Stannous Chloride	55.0%	150										2	1	1						2			2	1	2	1	2	1	1
Stannous Chloride	Sat.	75										1		1				1				1			1	1	1		1
Stannous Chloride	Sat.	120										1		1				1				1			1	1	1		1
Stearic Acid (Octadecanoic Acid)		100										1		1				1				1	1	1	1	1	1		1

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Stearic Acid (Octodecanoic Acid)		150										1		1									1	1		1	1		1
Stearyl Ether		150										1		1									1	1	1	1	1		1
Styrene		75		2	2	2	3	3	2		3	3	3	1		3	2	2	3	3	2	2	3	1	3	1	3	3	1
Sulfamic Acid	5.0%	100										1	1	1					1				1	1	1	1	1	1	1
Sulfamic Acid	5.0%	150										2	2	1						1			2	1	2	1	2	2	1
Sulfamic Acid	20.0%	100										1		1						1			1	1	1	1	1		1
Sulfamic Acid	20.0%	150										2	2	2						1					2	2	2	2	2
Sulfamic Acid	25.0%	100										1		1						1			1	1	1	1	1		1
Sulfamic Acid	25.0%	150										2	2	2									2	2	2	2	2	2	2
Sulfamic Acid	50.0%	100										1		1									1	1	1	1	1		1
Sulfamic Acid	Sat.	100										1	1	1											1	1	1	1	1
Sulfanilic Acid		100										1		1											1	1	1		1
Sulfite Liquor (paper)	75.0%	75										1		1				1				1	1	1	1	1	1		1
Sulfite Liquor (paper)	75.0%	120												1			1					1		1		1			1
Sulfonated Styrene Maleic Anhydride		100										1		1											1	1	1		1
Sulfonated Styrene Maleic Anhydride		150										1		1											1	1	1		1
Sulfonic Acid, Alkyl Benzene		75										3	1	3											3	3	3	1	3
Sulfonic Acid, p-nitrotoluene	24.0%	75											1														1		
Sulfur Chloride		100										3		2											3	2	3		2
Sulfur Dioxide		100										1		1				1				1	1	1	1	1	1		1
Sulfur Trioxide		100										1		1				1				1	1	1	1	1	1		1
Sulfuric Acid	1.0%	75			1		1	1	1		2	1	1	1			1	1	1	1	1	1	1	1	1	1	1	1	1
Sulfuric Acid	5.0%	75		1	1	1	1	1	1			1	1	1		1	1	1	1	1	1	1	2	1	1	1	1	1	1
Sulfuric Acid	5.0%	150			1			1				2	1	1			1	1		1	1	1	2	1	2	1	2	1	1
Sulfuric Acid	10.0%	75					1	1	1		2	1	1	1				1	1	1	1	1		1	1	1	1	1	1
Sulfuric Acid	10.0%	150			1			1				1	1	1			1	1	3		1	1		1	1	1	1	1	1
Sulfuric Acid	20.0%	75		2	1	2	1	1	1		2	1	1	1		2	1	1	2	1	1	1	1	1	1	1	1	1	1
Sulfuric Acid	25.0%	150						1				1	1	1						1	1			1	1	1	1	1	1
Sulfuric Acid	30.0%	75			1			1				1	1	1			1	1	2	1	1	1	1	1	1	1	1	1	1
Sulfuric Acid	40.0%	75			1			1				1	1	1			1	1	2	1	1	1	1	1	1	1	1	1	1

			* Double Veil Coat Recommended																										
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Sulfuric Acid	40.0%	150			1				1			1	2	1			1	1		1	1	1	1	1	1	1	1	2	1
Sulfuric Acid	50.0%	75		2	1	2	2	2	1	2	2	1	1	1		2	1	1	2	1	1	1	1	1	1	1	1	1	1
Sulfuric Acid	50.0%	150			1				1			1	2	1			1	2		1	1	2	1	2	1	2	1	2	1
Sulfuric Acid	70.0%	75			1		2	2	1			1	1	1			1	1		1	1	1	2	1	2	1	2	1	1
Sulfuric Acid	70.0%	150										2	1	2						2			2	2	2	2	2	1	2
Sulfuric Acid	75.0%	75			1		2	2	1		2	2	1	1			1	1		2	1	1	2	1	2	1	2	1	1
Sulfuric Acid	75.0%	150			2				2			3	2	2			2			2	2		2	2	3	2	3	2	2
Sulfuric Acid	77.0%	75			1		2	2	1			2	1	1			1	1		2	1	1	2	1	2	1	2	1	1
Sulfuric Acid	77.0%	150			2				2			3	2	2			2			3	2	2	2	2	3	2	3	2	2
Sulfuric Acid	80.0%	75			1				1			3	1	2			1			3	1		3	2	3	2	3	1	2
Sulfuric Acid	80.0%	150			2				2			4	3	2			2	3		3	2	3	4	2	4	2	4	3	2
Sulfuric Acid	86.0%	75		3	1	3			1			4	3	2		3	1			3	1		3	2	3	2	3	3	2
Sulfuric Acid	90.0%	75			1				1			4	4	2			1	2		3	1	2	4	3	4	3	4	4	3
Sulfuric Acid	93.0%	75			1				1			4	4	2			1	2		3	1	2	4	3	4	3	4	4	3
Sulfuric Acid	95.0%	75			1				1			4	4	3			1	2		4	1	2	4	4	4	4	4	4	4
Sulfuric Acid	98.0%	75			1		4	4	1		4	4	4	3			1	2		4	1	2	4	4	4	4	4	4	4
Sulfuric Acid - Fuming (Oleum)	20.0%	100			2				1					2			2	2			1	2		2		2			2
Sulfuric Acid - Fuming (Oleum)		100			1				1					3			1				1			3		3			3
Sulfuric Acid - Heptane - Water - Oil		75										1		1						1			1	1	1	1	1		1
Sulfuric Acid 20%, Hydrogen Peroxide 10%		75										1		1										1	1	1	1		1
Sulfuric Acid 20%, Nitric Acid 5%		75										1		1											1	1	1		1
Sulfuric Acid 25%, Hydrochloric Acid 10%		75										1		1											1	1	1		1
Sulfuric Acid 25%, Hydrofluoric Acid 10%		75										2*		1*											2*	1*	2*		1*
Sulfuric Acid 49%, Nitric Acid 35%		75			4				3				3	4			4				3					4		3	4
Sulfuric Acid 50%, Hydrochloric Acid 15%		75										2		1											2	1	2		1
Sulfurous Acid	2.0%	75										1		1									1	1	1	1	1		1

	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Sulfurous Acid	2.0%	150												1									1		1				1
Sulfurous Acid	6.0%	75										1		1									1	1	1	1	1		1
Sulfurous Acid	6.0%	150										2		2									2	2	2	2	2		2
Sulfurous Acid	10.0%	75										1	1	1											1	1	1	1	1
Sulfurous Acid	Sat.	75										2	1	2											2	2	2	1	2
Tall Oil		75			1		1	1	1		1			1			1	1	1		1	1	1	1	1	1	1		1
Tall Oil		100			1				1			1		1			1	1			1	1	1	1	1	1	1		1
Tall Oil		150			2				2			1		1			2	1		1	2	1	1	1	1	1	1		1
Tall Oil		180			2							1		1			2			2	2		1	1	1	1	1		1
Tall Oil		200										1		1									1	1	1	1	1		1
Tall Oil - Crude		100										1		1									1	1	1	1	1		1
Tannic Acid		100										1	1	1											1	1	1	1	1
Tannic Acid		120										1		1				1			1				1	1	1		1
Tartaric Acid	10.0%	75								2		1	1	1									1	1	1	1	1	1	1
Tartaric Acid	10.0%	120										1		1									1	1	1	1	1		1
Tartaric Acid		100											1	1										1		1		1	1
Tetrabutyltin		75										1		1										1	1	1	1		1
Tetrachloroethane		75										2		1				1				1		1	2	1	2		1
Tetrachloroethylene (Perchloroethylene)		75										2		1				2				2		1	2	1	2		1
Tetrachloroethylene (Perchloroethylene)		150										3		2				2				2			3	2	3		2
Tetrachloropentane		100										1		1											1	1	1		1
Tetrachloropyridine		100										2	1	1											2	1	2	1	1
Tetrahydrofuran (THF)	5.0%	75										2		1									2	1	2	1	2		1
Tetrahydrofuran (THF)		75			3		4	4	3		4	3		2			3	2	3		3	2	3	2	3	2	3		2
Tetrahydrofurfuryl Alcohol		75										2		1				2				2	2	1	2	1	2		1
Tetramethyl Ammonium Hydroxide	10.0%	75										1													1		1		
Tetramethyl Ammonium Hydroxide	40.0%	75										2													2		2		
Tetra-n-Butylphosphonium Hydroxide	40.0%	75										2													2		2		

* Double Veil Coat Recommended																													
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Tetrapotassium Pyrophosphate	60.0%	100										2	2	1											2	1	2	2	1
Tetrasodium Ethylenediaminetetraacetic Acid		100										1		1											1	1	1		1
Tetrasodium Pyrophosphate	5.0%	100										2	2												2		2	2	
Tetrasodium Pyrophosphate	Sat.	75										2													2		2		
Texanol		75					1	1	1		2	1		1				1		1		1			1	1	1		1
Thioglycol		75											2															2	
Thioglycolic Acid	10.0%	75										3		1									3	1	3	1	3		1
Thioglycolic Acid		75										3		2									3	2			3		2
Thionyl Chloride		75										3		2											3	2	3		2
Titanium Tetrachloride		100										1		1				1				1			1	1	1		1
Toluene		75		2	2	2	2	2	2		4	2	3	1		2	2	1	2	2	2	1	2	1	2	1	2	3	1
Toluene (2,4) Diisocyanate (Des N-75)		100										3	2	1										1	3	1	3	2	1
Toluene Sulfonic Acid-(p)	10.0%	150										1		1									1	1	1	1	1		1
Toluene Sulfonic Acid-(p)	25.0%	100										1		1			1					1	1	1	1	1	1		1
Toluene Sulfonic Acid-(p)	25.0%	150										2		2									2	2	2	2	2		2
Toluene Sulfonic Acid-(p)	65.0%	100										1	2	1				1				1	1	1	1	1	1	2	1
Toluene Sulfonic Acid-(p)	75.0%	100										1	2	1				1				1	1	1	1	1	1	2	1
Toluene Sulfonic Acid-(p)		100										1		1				1				1			1	1	1		1
Toluene Sulfonic Acid-(p)		120										2		1				2				2	2	1	2	1	2		1
Toluidine		75										3		2				2				2			3	2	3		2
Tributyl Phosphate		100					2	2				2		1						2			1	2	2	1	2		1
Trichloroacetic Acid	20.0%	100										1		1				2				2	1	1	1	1	1		1

			* Double Veil Coat Recommended																										
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662
Trichloroacetic Acid	40.0%	100										1	1	1											1	1	1	1	1
Trichloroacetic Acid	50.0%	100										1	2	1											1	1	1	2	1
Trichlorobenzene		75										3		1			1				1	3	1	3	1	3		1	
Trichloroethane 1,1,1 (Chloroethane)		75			2		3	3	2		3	3	3	1			2	2	3	3	2	2	2	1	3	1	3	3	1
Trichloroethylene		75										3		2			2				2	3	2	3	2	3		2	
Trichloromonofluoromethan e		75										2*		1*								2*	1*	2*	1*	2*		1*	
Tricresyl Phosphate		75										2		1			1				1			2	1	2		1	
Tricresyl Phosphate		120										1		1			1				1			1	1	1		1	
Triethanolamine		100										1		1								1	1	1	1	1		1	
Triethanolamine		150										2		2								2	2	2	2	2		2	
Triethyl Phosphite		100										2		2			1				1	2	2	2	2	2		2	
Triethylamine		75										2		1								2	1	2	1	2		1	
Triethylamine		100										2		2			2				2			2	2	2		2	
Triethylene Glycol		100											1	1											1		1	1	
Triethylenetetramine		100										2		1								2	1	2	1	2		1	
Trihydrobenzoic Acid	Sat.	75											2														2		
Trimethyl Benzene		75										2		1										2	1	2		1	
Trimethyl Carbinol		100											2														2		
Trimethylamine Hydrochloride		75										1	1											1		1	1		
Trimethyl Sulfonium Chloride		100										1		1										1	1	1		1	
Trimethylamine	20.0%	75										2		1										2	1	2		1	
Trimethylene Chlorobromide		75										3		2										3	2	3		2	
Trioctyl Phosphate		100										1		1										1	1	1		1	
Triphenyl Phosphite		75										1	1											1		1	1		
Tripropylene Glycol		100										1		1										1	1	1		1	
Trisodium Phosphate	15.0%	120										1		1								1	1	1	1	1		1	
Trisodium Phosphate	25.0%	100										1	1	1								1	1	1	1	1	1	1	
Trisodium Phosphate	Sat.	100										1	2	1			1				1	1	1	1	1	1	2	1	
Turpentine		75			1				1			1		1			1			1	1	1	1	1	1	1		1	
Turpentine		120										1		1			1				1		1	1	1	1		1	

* Double Veil Coat Recommended																														
	%	Temp (°F)	Flooring Systems	100	100 CR	133 Topcoat	310	330	330 CR	440	500	600	610	620	Lining / Coating Systems	150 / 150 TFE	150 CR	150 HT	230	260	260 CR	260 HT	640 / 640 AR	642 / 642 AR	650	652	660	661	662	
Urea		75			1		1	1	1		2	1	1	1			1	1	1	1	1	1	1	1	1	1	1	1	1	
Urea		100										1		1				1				1	1	1	1	1	1		1	
Urea		120										1		1											1	1	1		1	
Urea	30.0%	75			1				1			1					1				1				1		1			
Urea	50.0%	100			1				1			1	1	1			1				1		1	1	1	1	1	1	1	
Urea Ammonium Nitrate		100										1		1									1	1	1	1	1		1	
Urea Ammonium Nitrate		150										1		1									1	1	1	1	1		1	
Urea Formaldehyde Resin		75										2		1												2	1	2		1
Valeric Acid	5.0%	100										2		1									2	1			2		1	
Valeric Acid		100										2		1									2	1			2		1	
Valeric Acid		150										2		1									2	1			2		1	
Vinegar		100										1	1	1				1				1	1	1	1	1	1	1	1	
Vinyl Acetate	20.0%	100										2		2											2	2	2		2	
Vinyl Acetate		75										3		2				2				2	3	2	3	2	3		2	
Vinyl Chloride		75										3		2				2				2			3	2	3		2	
Vinyltoluene		75										2	2	1											2	1	2	2	1	
Water - DI		120		1	1	1	1	1	1			1		1			1	1		1	1	1	1	1	1	1	1		1	
Water - DI		150			1							1	1	1			1	1	2	1	1	1	1	1	1	1	1	1	1	
Water - DI		180										1	2	2									1	2	1	2	1	2	2	
Water - Sea		100										1		1				1		1		1			1	1	1		1	
Water - Tap		150										1		1					1				1	1	1	1	1		1	
Xylene		75			1				1			1		1			1	1		1	1	1	1	1	1	1	1		1	
Xylene		100		2	1				1			2	2	1			1	1	2	1	1	1	1	1	2	1	2	2	1	
Xylene		120			2							3	3	2			2	2		2	2	2				2	3	3	2	
Xylene		150			2							3	3	2			2			2	2					2	3	3	2	
Zinc Bromide	77.0%	75										1											1		1		1			
Zinc Chloride	40.0%	100										1	1	1						1					1	1	1	1	1	
Zinc Chloride	40.0%	150										1		1						1			1	1	1	1	1		1	
Zinc Chloride	Sat.	120										1	1	1				1				1			1	1	1	1	1	
Zinc Hydrosulfite	Sat.	100											2															2		
Zinc Nitrate	Sat.	100										1	1	1											1	1	1	1	1	
Zinc Sulfate	10.0%	120										1		1				1				1			1	1	1		1	
Zinc Sulfate		120										1		1				1				1			1	1	1		1	

* Double Veil Coat Recommended

%

Temp
(°F)

Flooring Systems

100

100 CR

133 Topcoat

310

330

330 CR

440

500

600

610

620

Lining / Coating
Systems

150 / 150 TFE

150 CR

150 HT

230

260

260 CR

260 HT

640 / 640 AR

642 / 642 AR

650

652

660

661

662

1 = Long Term Exposure (500 Hours Minimum)

2 = Short Term Exposure (Less Than 72 Hours)

3 = Splash And Spill (Less Than 8 Hours)

4 = Not Recommended For Direct Contact

Blank Box = No Test Data Available - Check with Greenstone

Technical Service for specific product recommendation.

* Double Veil Coat Recommended

Rev 1/21