



product data

SELECTION & SPECIFICATION DATA

TYPE & DESCRIPTION	Greenstone 370 CR Pourable Grout is a monolithic novolac epoxy system used to build or rebuild pump or tank pads, curbs, trenches, and column supports.
ADVANTAGES	Cures quickly to form an exceptionally tough, impact and abrasion resistant surface. Excellent adhesion to concrete, steel, and wood. Minimum down time. Sanitary, non-shrinking polymer system. Easy to clean - USDA acceptable.
CHEMICAL RESISTANCE	Not affected by water, oil, brine, most acids and alkalines. For specific recommendations, please refer to Greenstone's Chemical Resistance Guide.
USES	Used to build or rebuild pump or tank pads, curbs, trenches, and column supports.
GOVERNMENT AGENCY	Meets the requirements of the U.S. Department of Agriculture (USDA) for use as an incidental food contact flooring system.

FOR INDUSTRIAL USE ONLY!

PHYSICAL DATA	Compressive Strength, ASTM D695 - 16,500 psi (resin) Modulus of Elasticity, ASTM D695 - 1.062 X 10⁶ Tensile Strength, ASTM D638 - 1,750 psi (resin) Flexural Strength, ASTM D790 - 3,500 psi (resin) Thermal Coefficient of Linear Expansion, ASTM D696 - 6.16 X 10⁻⁶ in/in/°F. Bond Strength, ASTM C-321 - Greater than 350 psi (100% substrate failure). Impact Strength - 130 in/lbs. Indentation - MIL-D-3134F - No Indentation Water Absorption - ASTM C-413 - 0.047% Shelf Life - Minimum 12 months when storage temperature is between 70°F and 85°F. Working Time - approximately 40 minutes at 75°F. Potlife - 25 minutes at 75°F. Cure Time - Greenstone 370 CR Pourable Grout will harden in 8-12 hours at 75°F. The warmer the temperature, the faster it cures. Allow a minimum cure of 24 hours for light traffic, and 96 hours for heavy traffic loads and chemical spillage. Flammability - Does not support combustion Solids - 100% Color - Natural Gray
----------------------	---

PACKAGING / COVERAGE	370 CR POURABLE GROUT - packaged in batches the equivalent of approximately 1 cubic foot, consisting of - 1 container - Part A (resin) 1 container - Part B (hardener) 3 bags - Part C (chemical resistant aggregate)
-----------------------------	--

SUPPLEMENTAL PRODUCTS	150 CR Topcoat, 330 CR Mortar
------------------------------	--------------------------------------

SURFACE PREPARATION AND SUBSTRATES

SURFACE PREPARATION	New Concrete: must have a minimum of 28 days cure, and no curing agents or sealers shall be used. Remove oil, grease or other loose or foreign materials and contaminants. A good bonding tooth, the texture of rough sandpaper, is required to maximize adhesion, with the removal of all glaze. Examples of mechanical surface prep including, but not limited to - A. Sandblast with steel shot, fine silica, or other similar material. B. Wheel Abrader C. Scarify
----------------------------	---

Existing Concrete: remove all loose, weak concrete, and any paint wax, oil, grease or other contaminants. Once the concrete has been cleaned and neutralized, mechanical surface preparation shall be used to provide a good bonding tooth, a texture of rough sandpaper, with the removal of all glaze. Examples of mechanical surface preparation including, but not limited to -

- A. Sandblast with steel shot, fine silica, or other similar material.
- B. Wheel Abrader
- B. Scarify

Note: Holes and depressions 1/4" or deeper should be prefilled with 350 grout, or a similar system, prior to application. All surfaces must be dry prior to application of polymer system.

Metal Surfaces: Degrease surface prior to sandblasting. Use organic solvents, alkaline solutions, steam, hot water with detergents, or other systems that will completely remove dirt, oil, grease, etc. Blast the surface to near white SSPC-SP 10-70, or NACE No. 2 using a Venturi blast nozzle with 100psi air. To produce the 4 mil minimum anchor pattern or tooth, the blasting media used shall be a properly graded, clean, sharp angular abrasive similar to Humble Abrasive Flint S7 (6-30 mesh), Steel Grit (HG25), or Black Beauty (BB1040).

MIXING AND EQUIPMENT

MIXING

Pourable Grout - Empty the contents of Part B into Part A and mix thoroughly. When completed, empty the container into a mechanical mixer, draining the container for approximately 30 seconds. Start the mixer, and slowly add the Part C, chemical resistant aggregate, and mix the three components for approximately 3 minutes - until completely homogeneous. Note - Person mixing should wear a dust mask or respirator. **Important!** - The working life of the mixed blend is approximately 30 minutes. Always pour mixed batches as soon as possible. Mixed materials remaining in a container will produce heat. Keep away from combustible materials. Do not reseal mixed containers!

APPLICATION AND SAFETY

APPLICATION

GROUT: Cover the forms with plastic or release agent to minimize the bond between the 370 Pourable Grout and the form. Pour the material into the form slowly from one side and allow the material to seek its own level. The material can be vibrated by mechanical means to assist in air release from the polymer.

CURE TIME - Greenstone 370 CR Pourable Grout will harden in approximately 10 hours at 75°F. The warmer the temperature, the faster the cure. Allow 24 hours, at 75°F, for light traffic, and 96 hours for full cure.

CLEAN-UP - Cured or hardened Greenstone 370 CR Pourable Grout is almost impossible to remove. Clean tools and equipment immediately with hot soapy water, or a mixture of acetone and ethanol.

SAFETY

Observe good personal hygiene. Certain personnel may be sensitive to various types of resins which may cause dermatitis. Avoid contact with skin and breathing of vapor. Read and follow all caution statements on product info bulletin, material safety data sheet and container labels for this product. This bulletin provides standard information for the system and application procedure. Since varying application conditions may not be covered, consult GREENSTONE Technical Service Department for further information.

We guarantee our product to be free of defects in material and workmanship, and to be in accordance with our company quality control standards. All data, statements and recommendations made herein are based upon information we believe to be reliable, but are made without any representation or guarantee or warranty of accuracy and are made with reservation of all patent rights. Our products are sold on the condition that the user will evaluate them, as well as our recommendations, to determine their suitability for his own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only. No liability is assumed or implied, for injury to personnel, labor costs, product loss or any other expenses incidental to the structure or operation of the plant and equipment where the system is being applied.